

Quadrant EPP Fluorosint® MT-01 Enhanced PTFE (ASTM Product Data Sheet) (Unverified Data**)

Category : Polymer , Thermoplastic , Fluoropolymer , PTFE , Polytetrafluoroethylene (PTFE), Molded

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-Fluorosint-MT-01-Enhanced-PTFE-ASTM-Product-Data-Sheet-nbspUnverified-Data.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.27 g/cc	2.27 g/cc	ASTM D792
Water Absorption	0.10 %	0.10 %	Immersion, 24hr; ASTM D570(2)
Deformation	0.20 %	0.20 %	2000 psi; 122°F (50°C)

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	74	74	ASTM D785
Tensile Strength	14.5 MPa	2100 psi	ASTM D638
Elongation at Break	40 %	40 %	ASTM D638
Tensile Modulus	2.25 GPa	326 ksi	ASTM D638
Flexural Strength	27.6 MPa	4000 psi	ASTM D790
Flexural Modulus	3.34 GPa	485 ksi	ASTM D790
Compressive Strength	23.4 MPa	3400 psi	10% Def.; ASTM D695
Compressive Modulus	1.72 GPa	250 ksi	ASTM D695
Shear Strength	17.9 MPa	2600 psi	ASTM D732
Coefficient of Friction, Dynamic	0.18	0.18	dry vs. steel; QTM55007
K (wear) Factor	403 x 10 ⁻⁸ mm ³ /N-M	200 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	QTM55010
Limiting Pressure Velocity	0.158 MPa-m/sec	4500 psi-ft/min	4:1 safety factor applied; QTM 55010

Thermal Properties	Metric	English	Comments
CTE, linear	54.0 µm/m-°C @Temperature -40.0 - 150 °C	30.0 µin/in-°F @Temperature -40.0 - 302 °F	ASTM E831
Maximum Service Temperature, Air	316 °C	600 °F	Continuous

Thermal Properties	Metric	English	Comments
Flammability, UL94	V-0	V-0	
	@Thickness 3.17 mm	@Thickness 0.125 in	

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	<= 1.0e+6 ohm	<= 1.0e+6 ohm	ANSI/ESD STM 11.11

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Acceptable	Acceptable	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	No	No	
Continuous Sunlight	Acceptable	Acceptable	
Hot Water / Steam	Limited	Limited	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Acceptable	Acceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Acceptable	Acceptable	

Descriptive Properties	Value	Comments
Machinability	5	1-10, 1=Easier to Machine

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China