

Quadrant EPP Semitron® MP-370 (ASTM Product Data Sheet)

Category : Polymer , Thermoplastic

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-Semitron-MP-370-ASTM-Product-Data-Sheet.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.62 g/cc	1.62 g/cc	ASTM D792
Water Absorption	0.11 %	0.11 %	Immersion, 24hr; ASTM D570(2)
Water Absorption at Saturation	0.50 %	0.50 %	ASTM D570

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	98	98	ASTM D785
Tensile Strength	79.3 MPa	11500 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Tensile Modulus	4.41 GPa	640 ksi	ASTM D638
Flexural Strength	115.5 MPa	16750 psi	ASTM D790
Flexural Modulus	4.31 GPa	625 ksi	ASTM D790
Compressive Strength	125 MPa	18200 psi	10% Def.; ASTM D695
Compressive Modulus	4.14 GPa	600 ksi	ASTM D695
Shear Strength	77.9 MPa	11300 psi	ASTM D732
Izod Impact, Notched	0.214 J/cm	0.400 ft-lb/in	ASTM D256
K (wear) Factor	$\geq 1010 \times 10^{-8} \text{ mm}^3/\text{N-M}$	$\geq 500 \times 10^{-10} \text{ in}^3\text{-min/ft-lb-hr}$	QTM55010
Limiting Pressure Velocity	0.0771 MPa-m/sec	2200 psi-ft/min	4:1 safety factor; QTM 55007

Thermal Properties	Metric	English	Comments
CTE, linear	45.0 $\mu\text{m/m-}^\circ\text{C}$	25.0 $\mu\text{in/in-}^\circ\text{F}$	ASTM E831
	@Temperature -40.0 - 149 $^\circ\text{C}$	@Temperature -40.0 - 300 $^\circ\text{F}$	
Thermal Conductivity	0.340 W/m-K	2.36 BTU-in/hr-ft ² - $^\circ\text{F}$	ASTM F433
Melting Point	340 $^\circ\text{C}$	644 $^\circ\text{F}$	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	149 °C	300 °F	ASTM D648
Flammability, UL94	V-0 @Thickness 3.17 mm	V-0 @Thickness 0.125 in	Crystalline; ASTM D3418

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	EOS/ESD S11.11
Surface Resistivity per Square	>= 1.00e+13 ohm	>= 1.00e+13 ohm	EOS/ESD S11.11
Dielectric Constant	4.13 @Frequency 1.00e+6 Hz	4.13 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	14.8 kV/mm	376 kV/in	ASTM D149
Dissipation Factor	0.0040 @Frequency 1e+6 Hz	0.0040 @Frequency 1e+6 Hz	ASTM D150

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
Canada AG	No	No	
FDA	No	No	
NSF	No	No	
USDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Limited	Limited	
Acids, Weak	Acceptable	Acceptable	
Alcohols	Acceptable	Acceptable	
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	No	No	

Chemical Resistance Properties <i>Continuous Sunlight</i>	Metric <i>Limited</i>	English <i>Limited</i>	Comments
Hot Water / Steam	Acceptable	Acceptable	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Acceptable	Acceptable	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Acceptable	Acceptable	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China