

Quadrant EPP TIVAR® Dryslide PE-UHMW + internal lubricant + other additives (ISO Data)

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), UHMW PE Ultra High Molecular Weight

Material Notes:

Thanks to the lubricant built into a PE-UHMW matrix with higher molecular weight, TIVAR DrySlide offers a lower coefficient of friction and enhanced wear and abrasion resistance than TIVAR 1000. The additives used also make this material static dissipative and considerably improve UV-resistance Electro Static Dissipative Ideal for dusty environments Helps reduce surging Won't mark packaging or products Corrosion-resistant Self-lubricating Reduces noise No moisture absorption

Order this product through the following link:

http://www.lookpolymers.com/polymer_Quadrant-EPP-TIVAR-Dryslide-PE-UHMW-internal-lubricant-other-additives-ISO-Data.php

Physical Properties	Metric	English	Comments
Density	0.935 g/cc	0.0338 lb/in ³	ISO 1183-1
Water Absorption	<= 0.10 %	<= 0.10 %	96 hr; ISO 62
Moisture Absorption at Equilibrium	<= 0.10 %	<= 0.10 %	50% RH
Water Absorption at Saturation	<= 0.10 %	<= 0.10 %	ISO 62
Outgassing - Total Mass Loss	0.14 %	0.14 %	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	59	59	
Ball Indentation Hardness	32.0 MPa	4640 psi	ISO 2039-1
Tensile Strength	18.0 MPa	2610 psi	at Yield; ISO 527-1/-2
Elongation at Break	>= 50 %	>= 50 %	ISO 527-1/-2
Elongation at Yield	20 %	20 %	ISO 527-1/-2
Tensile Modulus	0.650 GPa	94.3 ksi	ISO 527-1/-2
Flexural Strength	16.0 MPa	2320 psi	
Compressive Strength	6.00 MPa	870 psi	ISO 604
	@Strain 1 %	@Strain 1 %	
	10.0 MPa	1450 psi	ISO 604
	@Strain 2 %	@Strain 2 %	
	16.0 MPa	2320 psi	ISO 604
	@Strain 5 %	@Strain 5 %	

Mechanical Properties	Metric	English	Comments
Charpy Impact Unnotched	NB	NB	ISO 179-1/1eU
Charpy Impact, Notched	10.0 J/cm ²	47.6 ft-lb/in ²	Partial Break; ISO 179-1/1eA
Coefficient of Friction, Dynamic	0.15 - 0.30	0.15 - 0.30	
Sand Slurry	85	85	
Limiting Pressure Velocity	0.0500 MPa-m/sec	1430 psi-ft/min	at 1 m/s unlubricated
	0.0800 MPa-m/sec	2280 psi-ft/min	at 0.1 m/s unlubricated

Thermal Properties	Metric	English	Comments
CTE, linear	200 µm/m-°C @ Temperature 23.0 - 100 °C	111 µin/in-°F @ Temperature 73.4 - 212 °F	
Thermal Conductivity	0.400 W/m-K	2.78 BTU-in/hr-ft ² -°F	
Melting Point	135 °C	275 °F	DSC, 10°C/min.; ISO 11357-1/-3
Maximum Service Temperature, Air	80.0 °C	176 °F	Continuous
Deflection Temperature at 1.8 MPa (264 psi)	42.0 °C	108 °F	ISO 75-1/-2
Flammability, UL94	HB	HB	
Oxygen Index	<= 20 %	<= 20 %	ISO 4589-1/-2

Electrical Properties	Metric	English	Comments
Surface Resistivity per Square	<= 1.0e+8 ohm	<= 1.0e+8 ohm	IEC 60093

Compliance Properties	Metric	English	Comments
3A-Dairy	No	No	
European Food 1935/2004	No	No	
FDA	No	No	
USP Class VI	No	No	

Chemical Resistance Properties	Metric	English	Comments
Acids, Strong (pH 1-3)	Acceptable	Acceptable	
Acids, Weak	Acceptable	Acceptable	

Chemical Resistance Properties	Metricable	Englishable	Comments
Alkalies, Strong (pH 11-14)	Acceptable	Acceptable	
Alkalies, Weak	Acceptable	Acceptable	
Chlorinated Solvents	Acceptable	Acceptable	
Conductive / Static Dissipative	Yes	Yes	
Continuous Sunlight	Limited	Limited	
Hot Water / Steam	Unacceptable	Unacceptable	
Hydrocarbons - Aliphatic	Acceptable	Acceptable	
Hydrocarbons - Aromatic	Limited	Limited	
Inorganic Salt Solutions	Acceptable	Acceptable	
Ketones, Esters	Acceptable	Acceptable	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China