

Qualchem Danamid AFGF-15 Polyamide 66, 15% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

Reinforced with glass fiberInformation provided by Qualchem Zrt.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Qualchem-Danamid-AFGF-15-Polyamide-66-15-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.26 g/cc	0.0455 lb/in ³	DIN 53479
Filler Content	13 - 17 %	13 - 17 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	<= 120 MPa	<= 17400 psi	50 mm/min; ISO 527-1,2
Elongation at Break	4.0 %	4.0 %	ISO 527-1,2
Charpy Impact Unnotched	<= 2.50 J/cm ² @Temperature 23.0 °C	<= 11.9 ft-lb/in ² @Temperature 73.4 °F	DIN 53453
Charpy Impact, Notched	<= 1.00 J/cm ² @Temperature -20.0 °C	<= 4.76 ft-lb/in ² @Temperature -4.00 °F	DIN 53453
	<= 1.00 J/cm ² @Temperature 23.0 °C	<= 4.76 ft-lb/in ² @Temperature 73.4 °F	DIN 53453

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	250 °C	482 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	220 °C	428 °F	DIN 53461
Flammability, UL94	HB @Thickness 4.00 mm	HB @Thickness 0.157 in	MSZ 10383

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	DIN 53482
Comparative Tracking Index	375 V	375 V	IEC 112

Processing Properties	Metric	English	Comments

Moisture Content	1.5~1.8 %	1.5~1.8 %	DIN 53714
Processing Properties	Metric	English	Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China