

Qualchem Danamid FGF-10 Polyamide 6, 10% Glass Fiber

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Reinforced with glass fiber.Information provided by Qualchem Zrt.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Qualchem-Danamid-FGF-10-Polyamide-6-10-Glass-Fiber.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in ³	DIN 53479
Filler Content	8.0 - 12 %	8.0 - 12 %	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	100 MPa	14500 psi	50 mm/min; ISO 527-1,2
Elongation at Break	4.0 %	4.0 %	ISO 527-1,2
Tensile Modulus	5.70 GPa	827 ksi	ISO 527-1,2
Flexural Strength	200 MPa	29000 psi	10mm/min; DIN 53452
Charpy Impact Unnotched	3.00 J/cm ² @Temperature 23.0 °C	14.3 ft-lb/in ² @Temperature 73.4 °F	DIN 53453
Charpy Impact, Notched	0.500 J/cm ² @Temperature 23.0 °C	2.38 ft-lb/in ² @Temperature 73.4 °F	DIN 53453

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	200 °C	392 °F	DIN 53461
Deflection Temperature at 1.8 MPa (264 psi)	180 °C	356 °F	DIN 53461
Flammability, UL94	HB @Thickness 4.00 mm	HB @Thickness 0.157 in	MSZ 10383

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	DIN 53482
Comparative Tracking Index	550 V	550 V	IEC 112

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Moisture Content	2.0 - 2.2 %	2.0 - 2.2 %	DIN 53714
Processing Properties	Metric	English	Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China