

RExtac Rextac® RT 5222 Amorphous Polyalphaolefin (APAO)

Category : Polymer , Thermoplastic , Polyalphaolefin , Polyolefin

Material Notes:

Modified Bitumen Roofing Grade. Description: High molecular weight REXtac, ethylene copolymer, and FDA compliant. Features: High viscosity and low crystallinity. Applications: Component of modified bitumen roofing systems. Other Properties: Ring and Ball Softening Point (ASTM E 28): 138°C. Needle Penetration (ASTM D 1321): 26 mm. Melt Density (190°C; Huntsman Method): 0.74 g/cc. Flashpoint, COC (ASTM D 93): >235°C. Information provided by Huntsman Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_REXtac-Rextac-RT-5222-Amorphous-Polyalphaolefin-APAO.php

Physical Properties	Metric	English	Comments
Density	0.860 g/cc	0.0311 lb/in ³	ASTM D 792
Viscosity	356000 cP @Temperature 190 °C	356000 cP @Temperature 374 °F	melt viscosity; ASTM D 3236

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	-26.3 °C	-15.3 °F	ASTM D3417

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China