

Radici Radiflam® A RV250AF (cond.) Nylon 66-25GF

Category : Polymer , Thermoplastic , Nylon , Nylon 66 , Nylon 66, 30% Glass Fiber Filled

Material Notes:

Radiflam® A is a range of flame retardant polyamides 66 (PA 66) used for injection molding and extrusion for all applications where high fire resistance is required. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radiflam-A-RV250AF-cond-Nylon-66-25GF.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.44 g/cc	1.44 g/cc	(Dry)
Water Absorption	5.6 %	5.6 %	initially dry
Moisture Absorption at Equilibrium	1.4 %	1.4 %	initially dry

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	90.0 MPa	13100 psi	
Elongation at Break	3.0 %	3.0 %	
Tensile Modulus	5.20 GPa	754 ksi	
Charpy Impact Unnotched	5.20 J/cm ²	24.7 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	6.20 J/cm ²	29.5 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.570 J/cm ²	2.71 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.10 J/cm ²	5.23 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	260 °C	500 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	600 V	600 V	

Electrical Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China