

Radici Radilon® S 35HR (cond.) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , Unreinforced

Material Notes:

PA6 medium-high viscosity injection molding grade. Easy mould release. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-S-35HR-cond-Nylon-6.php

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	45.0 MPa	6530 psi	
Elongation at Break	>= 50 %	>= 50 %	Nominal
Elongation at Yield	30 %	30 %	
Tensile Modulus	1.25 GPa	181 ksi	
Charpy Impact Unnotched	NB	NB	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	NB	NB	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	0.400 J/cm²	1.90 ft-lb/in²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	2.20 J/cm²	10.5 ft-lb/in²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China