

Radici Radilon® S 40FL (dry) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6, Film Grade

Material Notes:

Radilon® S (homopolyamides) are normally used in cast and blown extrusion for the production of packaging films. Radilon® S grades can be extruded to a thickness varying from 20 mm to 100 mm. Application: Cast/blown film extrusion Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-S-40FL-dry-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ISO 1183
Viscosity Measurement	245	245	cm³/g Viscosity Number; ISO 307

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	80.0 MPa	11600 psi	ISO 5271/2
Elongation at Break	4.0 %	4.0 %	ISO 5271/2
Tensile Modulus	2.95 GPa	428 ksi	ISO 5271/2
Flexural Strength	100 MPa	14500 psi	ISO 178
Flexural Modulus	2.40 GPa	348 ksi	ISO 178

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	ISO 11357-1

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.060 %	<= 0.060 %	ISO 960D

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China