

Radici Radilon® S RCV3015 (cond.) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Radilon® S is a range of polyamide 6 (PA6) products obtained through the polymerization of caprolactam and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-S-RCV3015-cond-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	(Dry)
Water Absorption	7.9 %	7.9 %	initially dry
Moisture Absorption at Equilibrium	2.2 %	2.2 %	initially dry
Viscosity Measurement	140	140	cm ³ /g Viscosity Number

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	85.0 MPa	12300 psi	
Elongation at Break	9.5 %	9.5 %	Nominal
Elongation at Yield	3.9 %	3.9 %	
Tensile Modulus	6.10 GPa	885 ksi	
Charpy Impact Unnotched	3.80 J/cm ²	18.1 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	7.00 J/cm ²	33.3 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	0.430 J/cm ²	2.05 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	0.850 J/cm ²	4.04 ft-lb/in ²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	(Dry)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 ohm-cm	1.00e+11 ohm-cm	

Electrical Properties	Metric	English	Comments
Surface Resistance	1.00×10^{14} ohm	1.00×10^{14} ohm	
Comparative Tracking Index	550 V	550 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China