

Radici Radilon® S RV300LK (dry) Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6

Material Notes:

Radilon® S is a range of polyamide 6 (PA6) products obtained through the polymerization of caprolactam and used for injection, extrusion and blow-molding. Information provided by Radici group.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Radici-Radilon-S-RV300LK-dry-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.35 g/cc	1.35 g/cc	
Water Absorption	7.0 %	7.0 %	
Moisture Absorption at Equilibrium	2.0 %	2.0 %	
Viscosity Measurement	160	160	cm³/g Viscosity Number

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	165 MPa	23900 psi	
Elongation at Break	3.8 %	3.8 %	
Tensile Modulus	9.15 GPa	1330 ksi	
Charpy Impact Unnotched	8.00 J/cm²	38.1 ft-lb/in²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	9.50 J/cm²	45.2 ft-lb/in²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Charpy Impact, Notched	1.40 J/cm²	6.66 ft-lb/in²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	1.60 J/cm²	7.61 ft-lb/in²	
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Melting Point	220 °C	428 °F	
Deflection Temperature at 0.46 MPa (66 psi)	215 °C	419 °F	
Deflection Temperature at 1.8 MPa (264 psi)	200 °C	392 °F	

Thermal Properties	210 °C Metric	410 °F English	Comments
	@Load 5.10 kg	@Load 11.2 lb	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	HB	HB	
	@Thickness 0.800 mm	@Thickness 0.0315 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+11$ ohm-cm	$\geq 1.00\text{e}+11$ ohm-cm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China