

Raschig Group MELOPLAS® 150 MF

Category : Polymer , Thermoset , Melamine , Melamine-Phenolic Copolymer , Phenolic

Material Notes:

Wood flour-reinforced MF molding compound in dark colors. High surface hardness, high mechanical strength, good electrical properties. Self-extinguishing (V-O/1,6 according to UL 94), UL-listed. Free of halogens and toxic heavy metals. Supervised according ISO 14528-3 DIN 7708: MF 150 ISO 800: MF B20 ISO 14528-3: MF (WD30+MD15) - (WD40+MD05). Forms: Low dust granulate packed in moisture resistant bags Standard bag size: 25 kg palletized in 1.000 kg loads or big-bags. Processing: Injection or compression. Applications: Molded parts in electrical engineering. Fittings for household appliances. Car ash-trays. Information provided by the Raschig Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Raschig-Group-MELOPLAS-150-MF.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.50 - 1.70 g/cc	1.50 - 1.70 g/cc	ISO 1183
Apparent Bulk Density	0.500 - 0.700 g/cc	0.0181 - 0.0253 lb/in ³	ISO 60
Water Absorption	<= 2.0 % @Temperature 23.0 °C, Time 86400 sec	<= 2.0 % @Temperature 73.4 °F, Time 24.0 hour	ISO 62
Linear Mold Shrinkage	0.0050 - 0.010 cm/cm	0.0050 - 0.010 in/in	(longitudinal) Compression; ISO 2577
	0.0080 - 0.013 cm/cm	0.0080 - 0.013 in/in	(longitudinal) Injection; ISO 2257

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	40.0 - 50.0 MPa	5800 - 7250 psi	Compression; ISO 527
	50.0 - 75.0 MPa	7250 - 10900 psi	Injection; ISO 527
Modulus of Elasticity	5.00 - 8.00 GPa	725 - 1160 ksi	Injection and Compression; ISO 527
Flexural Strength	70.0 - 100 MPa	10200 - 14500 psi	Compression; ISO 178
	90.0 - 120 MPa	13100 - 17400 psi	Injection; ISO 178
Flexural Modulus	8.00 - 9.00 GPa	1160 - 1310 ksi	Injection and Compression; ISO 178
Compressive Strength	200 - 250 MPa	29000 - 36300 psi	Injection and Compression; ISO 604
Charpy Impact Unnotched	0.500 - 0.700 J/cm ² @Temperature 23.0 °C	2.38 - 3.33 ft-lb/in ² @Temperature 73.4 °F	Compression; ISO 179/ 1eU
	0.700 - 1.00 J/cm ² @Temperature 23.0 °C	3.33 - 4.76 ft-lb/in ² @Temperature 73.4 °F	Injection; ISO 179/ 1eU
	0.120 - 0.180 J/cm ²	0.571 - 0.857 ft-lb/in ²	

Charpy Impact, Notched Mechanical Properties	Metric @ Temperature 23.0 °C	English @ Temperature 73.4 °F	Compression; ISO 179/ 1eA Comments
	0.130 - 0.200 J/cm²	0.619 - 0.952 ft-lb/in²	Injection; ISO 179/ 1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	15.0 - 35.0 µm/m-°C @Temperature 50.0 - 100 °C	8.33 - 19.4 µin/in-°F @Temperature 122 - 212 °F	longitudinal; ISO 11359-2
Thermal Conductivity	0.400 - 0.500 W/m-K	2.78 - 3.47 BTU-in/hr-ft²-°F	ASTM E1461
Maximum Service Temperature, Air	135 °C	275 °F	20,000 h; IEC 60216/T1
	160 °C	320 °F	< 50 h; IEC 60216/T1
Deflection Temperature at 1.8 MPa (264 psi)	155 - 180 °C	311 - 356 °F	Injection and Compression; ISO 75
Deflection Temperature at 8.0 MPa	110 - 130 °C	230 - 266 °F	Injection and Compression; ISO 75
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	
	5VB @Thickness 1.50 mm	5VB @Thickness 0.0591 in	
Shrinkage	1.0 - 1.5 % @Temperature 110 °C, Time 605000 sec	1.0 - 1.5 % @Temperature 230 °F, Time 168 hour	ISO 2577

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+11 - 1.00e+12 ohm-cm	1.00e+11 - 1.00e+12 ohm-cm	IEC 60093
Surface Resistance	1.00e+10 - 1.00e+11 ohm	1.00e+10 - 1.00e+11 ohm	IEC 60093
Dielectric Constant	7.0 - 9.0 @Frequency 1.00e+6 Hz	7.0 - 9.0 @Frequency 1.00e+6 Hz	IEC 60250
	11 - 16 @Frequency 100 Hz	11 - 16 @Frequency 100 Hz	IEC 60250
Dielectric Strength	15.0 - 20.0 kV/mm	381 - 508 kV/in	IEC 60243-1
	0.030 - 0.050	0.030 - 0.050	

Electrical Properties	Metric	English	Comments
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	0.30 - 0.50	0.30 - 0.50	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Arc Resistance	115 - 125 sec	115 - 125 sec	ASTM D495
Comparative Tracking Index	>= 600 V	>= 600 V	CTI; IEC 60112

Processing Properties	Metric	English	Comments
	6.00 Month	6.00 Month	
Shelf Life	@Temperature 15.0 - 25.0 °C	@Temperature 59.0 - 77.0 °F	

Descriptive Properties	Value	Comments
Arc Resistance	5 Stufe	ASTM D495
Glow wire flammability test	960/1	IEC 60695 2-12
Glow wire ignitability test	900/1	IEC 60695 2-13
Water Absorption	<115 mg	ISO 62; 24h / 23°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China