

Raschig Group RALUPOL® 4806 UP

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Polyester, TS

Material Notes:

Glass-fiber reinforced polyester molding compound. Very low mold shrinkage and post-shrinkage, very good mechanical strength, very good electrical values, better performance values compared to UP 804. This product meets the allowed upper limits for heavy metals and PCAs and also conforms to the requirements of the EU directives 2002/95 (RoHS), 2002/96 (WEEE) and 2006/122 (PFOS). Processing: Injection and compression molding Primary application: Contact bridges, Relays, Circuit breakers (RCD/MCB) Information provided by the Raschig Group

Order this product through the following link:

http://www.lookpolymers.com/polymer_Raschig-Group-RALUPOL-4806-UP.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.90 - 2.10 g/cc	1.90 - 2.10 g/cc	ISO 1183
Apparent Bulk Density	0.750 - 0.950 g/cc	0.0271 - 0.0343 lb/in³	ISO 60
Water Absorption	<= 0.50 % @Temperature 23.0 °C, Time 86400 sec	<= 0.50 % @Temperature 73.4 °F, Time 24.0 hour	ISO 62
Linear Mold Shrinkage	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	Compression; ISO 2577
	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	Injection; ISO 2257

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	35.0 - 60.0 MPa	5080 - 8700 psi	Compression; ISO 527
	40.0 - 70.0 MPa	5800 - 10200 psi	Injection; ISO 527
Modulus of Elasticity	9.00 - 11.0 GPa	1310 - 1600 ksi	Injection and Compression; ISO 527
Flexural Strength	70.0 - 100 MPa	10200 - 14500 psi	Compression; ISO 178
	110 - 130 MPa	16000 - 18900 psi	Injection; ISO 178
Flexural Modulus	10.0 - 13.0 GPa	1450 - 1890 ksi	Compression; ISO 178
	13.0 - 16.0 GPa	1890 - 2320 ksi	Injection; ISO 178
Compressive Strength	150 - 200 MPa	21800 - 29000 psi	ISO 604
Charpy Impact Unnotched	0.500 - 1.00 J/cm² @Temperature 23.0 °C	2.38 - 4.76 ft-lb/in² @Temperature 73.4 °F	Compression; ISO 179/ 1eU
	0.700 - 1.00 J/cm² @Temperature 23.0 °C	3.33 - 4.76 ft-lb/in² @Temperature 73.4 °F	Injection; ISO 179/ 1eU

Mechanical Properties	Metric	English	Comments
Charpy Impact, Notched	0.250 - 0.350 J/cm ²	1.94 - 1.67 ft-lb/in ²	Compression; ISO 179/ 1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	
	0.350 - 0.500 J/cm ²	1.67 - 2.38 ft-lb/in ²	Injection; ISO 179/ 1eA
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear	10.0 - 20.0 µm/m-°C	5.56 - 11.1 µin/in-°F	ISO 11359-2
	@Temperature 50.0 - 100 °C	@Temperature 122 - 212 °F	
Thermal Conductivity	0.900 - 1.10 W/m-K	6.25 - 7.63 BTU-in/hr-ft ² -°F	DIN 52 612
Maximum Service Temperature, Air	170 °C	338 °F	20,000 h; IEC 216/T1
	220 °C	428 °F	< 50 h; IEC 216/T1
Deflection Temperature at 8.0 MPa	>= 200 °C	>= 392 °F	Compression and Injection; ISO 75-C
Flammability, UL94	V-0	V-0	
	@Thickness 1.50 mm	@Thickness 0.0591 in	
Shrinkage	<= 0.10 %	<= 0.10 %	Post Shrinkage; ISO 2577
	@Temperature 110 °C, Time 605000 sec	@Temperature 230 °F, Time 168 hour	

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+14 - 1.00e+15 ohm-cm	1.00e+14 - 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	1.00e+13 - 1.00e+14 ohm	1.00e+13 - 1.00e+14 ohm	IEC 60093
Dielectric Constant	4.0 - 5.0	4.0 - 5.0	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	5.0 - 6.0	5.0 - 6.0	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	25.0 - 35.0 kV/mm	635 - 889 kV/in	IEC 60243-1
Dissipation Factor	0.010 - 0.030	0.010 - 0.030	IEC 60250
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.010 - 0.030	0.010 - 0.030	

Electrical Properties	Metric	English	Comments
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	IEC 60250
Comparative Tracking Index	600 V	600 V	PTI; IEC 60112

Processing Properties	Metric	English	Comments
Shelf Life	6.00 Month @Temperature 15.0 - 25.0 °C	6.00 Month @Temperature 59.0 - 77.0 °F	

Descriptive Properties	Value	Comments
Arc Resistance	4 Stufe	ASTM D495
Glow wire ignitability test	930/1	IEC 60695 2-13
Glow-wire flammability test	960/1	IEC 60695 2-12
Water Absorption	<35 mg	ISO 62; 24h / 23°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China