

Reliance Industries LLDPE film - 1 MI O-LLDPE films

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

Material Notes:

Information provided by Reliance Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reliance-Industries-LLDPE-film-1-MI-O-LLDPE-films.php

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	700 %	700 %	
Film Elongation at Break, TD	800 %	800 %	
Elmendorf Tear Strength, MD	15.0 g/micron	381 g/mil	
Elmendorf Tear Strength, TD	24.0 g/micron	610 g/mil	
Dart Drop	9.00 g/micron	229 g/mil	
Film Tensile Strength at Break, MD	48.0 MPa	6960 psi	
Film Tensile Strength at Break, TD	43.0 MPa	6240 psi	

Optical Properties	Metric	English	Comments
Haze	23 %	23 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China