

## Reliance Industries LLDPE film - Zeolite based film

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

### Material Notes:

Information provided by Reliance Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Reliance-Industries-LLDPE-film-Zeolite-based-film.php](http://www.lookpolymers.com/polymer_Reliance-Industries-LLDPE-film-Zeolite-based-film.php)

| Mechanical Properties              | Metric        | English   | Comments |
|------------------------------------|---------------|-----------|----------|
| Film Elongation at Break, MD       | 500 %         | 500 %     |          |
| Film Elongation at Break, TD       | 680 %         | 680 %     |          |
| Elmendorf Tear Strength, MD        | 12.0 g/micron | 305 g/mil |          |
| Elmendorf Tear Strength, TD        | 22.0 g/micron | 559 g/mil |          |
| Dart Drop                          | 7.00 g/micron | 178 g/mil |          |
| Film Tensile Strength at Break, MD | 34.0 MPa      | 4930 psi  |          |
| Film Tensile Strength at Break, TD | 27.0 MPa      | 3920 psi  |          |

| Optical Properties | Metric | English | Comments |
|--------------------|--------|---------|----------|
| Haze               | 50 %   | 50 %    |          |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China