

Reliance Industries Polypropylene - Suzorite mica (untreated) filler

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Mica Filler

Material Notes:

Information provided by Reliance Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Reliance-Industries-Polypropylene-Suzorite-mica-untreated-filler.php

Physical Properties	Metric	English	Comments
Linear Mold Shrinkage	0.0080 cm/cm	0.0080 in/in	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.0 MPa	4060 psi	
Flexural Strength	45.0 MPa	6530 psi	
Flexural Modulus	<= 6.40 GPa	<= 928 ksi	
Izod Impact, Notched	0.320 J/cm	0.600 ft-lb/in	
Izod Impact, Unnotched	2.03 J/cm	3.80 ft-lb/in	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	89.0 °C	192 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China