

Resinlab® CYNERGY CA6304 Adhesive

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

Material Notes:

Description: The CYNERGY 6300 SERIES products are for use in applications where a faster set time is desired or low moisture conditions exist. Provides good bonds to a wide variety of materials. Application: The CYNERGY SERIES of the cyanoacrylates should be applied in small amounts to one surface only. The parts should then be mated together under slight pressure. This causes the adhesive to spread out into a thin film and assures optimum adhesive performance. The pressure need only be applied for several seconds. The CYNERGY SERIES cures rapidly allowing for bonded parts to be handled within 10 to 60 seconds for most applications. Full cure is normally within 24 hours. Information Provided by Resinlab L.L.C., an Ellsworth Adhesives Company.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resinlab-CYNERGY-CA6304-Adhesive.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.05 g/cc	1.05 g/cc	
Viscosity	500 cP	500 cP	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	18.6 MPa	2700 psi	
Adhesive Bond Strength	29.0 MPa	4200 psi	Steel lap shear

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	93.3 °C	200 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	>= 0.0833 min	>= 0.00139 hour	Fixture
	240 min	4.00 hour	Full cure

Descriptive Properties	Value	Comments
Base	Ethyl	
Color	Clear	
Gap Fill (mil)	7	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China