## **Resinlab® TL5021 Anaerobic Threadlocking Compound**

Category : Polymer , Adhesive

## Material Notes:

The TL5000 Series anaerobic threadlocking compounds are designed for use in demanding applications to fill the spaces and surface irregularities between tightly mated cylindrical parts. They form a tough permanent bonds which greatly enhances the torque and pullout strength. These products are highly resistant to heat, corrosion, vibration, water gases, oils and many other chemicals. They are single component solvent free materials manufactured in a wide variety of viscosities to satisfy specific bonding applications. This technology increases the reliability and performance of assemblies while reducing dependence upon maintaining costly tight machining tolerances. Information Provided by Resinlab L.L.C., an Ellsworth Adhesives Company.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Resinlab-TL5021-Anaerobic-Threadlocking-Compound.php

| Physical Properties | Metric    | English   | Comments |
|---------------------|-----------|-----------|----------|
| Specific Gravity    | 1.08 g/cc | 1.08 g/cc |          |
| Viscosity           | 200 cP    | 200 cP    |          |

| Thermal Properties               | Metric   | English  | Comments |
|----------------------------------|----------|----------|----------|
| Maximum Service Temperature, Air | 350 °C   | 662 °F   |          |
| Minimum Service Temperature, Air | -60.0 °C | -76.0 °F |          |

| Processing Properties | Metric   | English    | Comments  |
|-----------------------|----------|------------|-----------|
| Cure Time             | 10.0 min | 0.167 hour | Fixture   |
|                       | 480 min  | 8.00 hour  | Full Cure |

| Descriptive Properties | Value  | Comments          |
|------------------------|--------|-------------------|
| Color                  | Violet |                   |
| Thixotropy             | Low    |                   |
| Torque (ft*lbs)        | 25     | Prevailing Torque |
|                        | 40     | Breakaway Torque  |

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842



Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China