

Resinoid 1370 Phenolic Molding, Glass Reinforced

Category : Polymer , Thermoset , Filled/Reinforced Thermoset , Phenolic , Phenolic, Novolac, Glass Filled

Material Notes:

Data provided by the manufacturer. The Resinoid 1300 and 7000 glass fiber reinforced series compounds feature mechanical strength, dimensional stability, electrical insulation, and heat resistance

Order this product through the following link:

http://www.lookpolymers.com/polymer_Resinoid-1370-Phenolic-Molding-Glass-Reinforced.php

Physical Properties	Metric	English	Comments
Density	1.85 g/cc	0.0668 lb/in ³	ASTM D792A
Water Absorption	0.10 %	0.10 %	24 hours R.T. ASTM D570

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	52.0 MPa	7540 psi	ASTM D651
Flexural Strength	90.0 MPa	13100 psi	ASTM D790
Flexural Modulus	16.0 GPa	2320 ksi	ASTM D790
Compressive Strength	200 MPa	29000 psi	ASTM D695
Izod Impact, Notched	0.578 J/cm	1.08 ft-lb/in	ASTM D256A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	>= 300 °C	>= 572 °F	ASTM D648

Electrical Properties	Metric	English	Comments
Dielectric Strength	9.40 kV/mm	239 kV/in	Short Time; Dry; ASTM D149

Processing Properties	Metric	English	Comments
Mold Temperature	155 - 180 °C	311 - 356 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China