

RheTech Products T10P250-00 10% Talc Reinforced Polypropylene Copolymer, Natural

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Talc Filler

Material Notes:

Applications: Fan shroudsCenter consolesAir ductsInjection molding conditions reported in table.Information provided by RheTech Products.

Order this product through the following link:

http://www.lookpolymers.com/polymer_RheTech-Products-T10P250-00-10-Talc-Reinforced-Polypropylene-Copolymer-Natural.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.970 g/cc	0.970 g/cc	23/23°C; ASTM D792
Filler Content	10 %	10 %	ASTM D5630
Linear Mold Shrinkage	0.0135 cm/cm	0.0135 in/in	ASTM D955
Melt Flow	6.0 g/10 min @Load 2.16 kg, Temperature 230 °C	6.0 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	70	70	ASTM D2240
Tensile Strength at Break	26.2 MPa	3800 psi	2 in/min; ASTM D638
Flexural Modulus	1.65 GPa	240 ksi	Tangent; ASTM D790
Izod Impact, Notched	0.747 J/cm @Temperature 23.0 °C	1.40 ft-lb/in @Temperature 73.4 °F	ASTM D256
Gardner Impact	10.2 J	7.50 ft-lb	ASTM D5420

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	220 °F	ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	60.0 °C	140 °F	ASTM D648

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	193 - 221 °C	380 - 430 °F	
Middle Barrel Temperature	199 - 227 °C	390 - 440 °F	
Front Barrel Temperature	204 - 232 °C	400 - 450 °F	

Processing Properties	Metric	English	Comments
Nozzle Temperature	210 - 221 °C	410 - 430 °F	
Mold Temperature	26.7 - 48.9 °C	80.0 - 120 °F	
Drying Temperature	65.6 - 82.2 °C	150 - 180 °F	
Dry Time	1 - 2 hour	1 - 2 hour	
Moisture Content	<= 0.050 %	<= 0.050 %	Recommended
Injection Pressure	55.2 - 103 MPa	8000 - 15000 psi	
Hold Pressure	27.6 - 51.7 MPa	4000 - 7500 psi	
Back Pressure	0.345 - 1.03 MPa	50.0 - 150 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China