

Rogers Corporation Poron® ThinStik™ 92-09020 Self-Adhesive Urethane Foam

Category : Polymer , Thermoset , Polyurethane, TS , Thermoset Polyurethane Foam, Unreinforced

Material Notes:

PORON® ThinStik™ materials utilize an acrylic pressure sensitive adhesive manufactured to Roger's specifications. This adhesive provides reliable bonding to a wide variety of substrates, exhibits high quality optical clarity, withstands a wide range of temperatures and is resistant to chemical exposure. Color: Black Information provided by Rogers Corporation.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Rogers-Corporation-Poron-ThinStik-92-09020-Self-Adhesive-Urethane-Foam.php

Physical Properties	Metric	English	Comments
Density	0.144 g/cc	0.00521 lb/in ³	ASTM D3574-95 Test A

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	78 %	78 %	ASTM D882
	74 %	74 %	80% RH; ASTM D882
	@Temperature 66.0 °C, Time 346000 sec	@Temperature 151 °F, Time 96.0 hour	
Film Elongation at Break, TD	32 %	32 %	ASTM D882
	66 %	66 %	80% RH; ASTM D882
	@Temperature 66.0 °C, Time 346000 sec	@Temperature 151 °F, Time 96.0 hour	
Compressive Yield Strength	0.00552 MPa	0.800 psi	0.2"/min. strain rate
	@Strain 25.0 %	@Strain 25.0 %	
Tear Strength	0.310 kN/m	1.77 pli	Peel Adhesion, 180° Peel, to Polypropylene; ASTM D1000
	@Time 1190 sec	@Time 0.330 hour	
	0.320 kN/m	1.83 pli	Peel Adhesion, 180° Peel, to Stainless Steel; ASTM D1000
	@Time 1190 sec	@Time 0.330 hour	
	0.320 kN/m	1.83 pli	Peel Adhesion, 180° Peel, to Polypropylene; ASTM D1000
	@Time 259000 sec	@Time 72.0 hour	
	0.330 kN/m	1.88 pli	Peel Adhesion, 180° Peel, to ABS; ASTM D1000
	@Time 1190 sec	@Time 0.330 hour	
	0.330 kN/m	1.88 pli	Peel Adhesion, 180° Peel, to Acrylic; ASTM D1000
	@Time 1190 sec	@Time 0.330 hour	
	0.340 kN/m	1.94 pli	Peel Adhesion, 180° Peel, to

Mechanical Properties	Metric @ Time 1190 sec	English @ Time 0.330 hour	Polycarbonate; ASTM D1000 Comments
	0.360 kN/m @Time 259000 sec	2.05 pli @Time 72.0 hour	Peel Adhesion, 180° Peel, to Stainless Steel; ASTM D1000
	0.390 kN/m @Time 259000 sec	2.23 pli @Time 72.0 hour	Peel Adhesion, 180° Peel, to ABS; ASTM D1000
	0.390 kN/m @Time 259000 sec	2.23 pli @Time 72.0 hour	Peel Adhesion, 180° Peel, to Acrylic; ASTM D1000
	0.404 kN/m @Time 259000 sec	2.31 pli @Time 72.0 hour	Peel Adhesion, 180° Peel, to Polycarbonate; ASTM D1000
Compression Set	<= 5.0 % @Temperature 23.0 °C	<= 5.0 % @Temperature 73.4 °F	ASTM D3574-95 Test D
	<= 10 % @Temperature 70.0 °C	<= 10 % @Temperature 158 °F	ASTM D3574-95 Test D
Seal Strength	9.40 g/25 mm	9.40 g/in	Release Adhesion, 180° Peel; ASTM D1000
	10.6 g/25 mm @Temperature 66.0 °C, Time 346000 sec	10.6 g/in @Temperature 151 °F, Time 96.0 hour	Release Adhesion, 180° Peel, 80% RH; ASTM D1000

Descriptive Properties	Value	Comments
Tack	411 g	ASTM D2979 (1 second dwell), 96 hours at 66°C/80% RH
	424 g	ASTM D2979 (1 second dwell)
Tensile, CMD (lb) per ASTM D882	5	80% RH; 66°C; 96 hr
	9.1	
Tensile, MD (lb) per ASTM D882	11.4	80% RH; 66°C; 96 hr
	12	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China