

Rotuba 860H Ethyl Cellulose

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Ethyl Cellulose, Molded

Material Notes:

Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Rotuba-860H-Ethyl-Cellulose.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in³	ASTM D792-60T

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	110	110	ASTM D785
Tensile Strength, Ultimate	44.0 MPa	6380 psi	ASTM D638-61T
Elongation at Break	23 %	23 %	ASTM D638-61T
Izod Impact, Notched	1.07 J/cm	2.00 ft-lb/in	ASTM D256-56
	0.270 J/cm	0.506 ft-lb/in	ASTM D256
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	152 °C	306 °F	Flow temperature, ASTM D569-59
Deflection Temperature at 0.46 MPa (66 psi)	93.0 °C	199 °F	ASTM D648-56

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.18	3.18	ASTM D150-54T
	@Frequency 10000 Hz	@Frequency 10000 Hz	
	3.23	3.23	ASTM D150-54T
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dissipation Factor	0.0072	0.0072	ASTM D150-54T
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.0127	0.0127	ASTM D150-54T
	@Frequency 10000 Hz	@Frequency 10000 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China