

Rotuba 880 Ethyl Cellulose

Category : Polymer , Renewable/Recycled Polymer , Thermoplastic , Cellulosic , Ethyl Cellulose, Molded

Material Notes:

Data provided by the manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Rotuba-880-Ethyl-Cellulose.php

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in ³	ASTM D792-60T

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	53	53	ASTM D785
Tensile Strength, Ultimate	21.0 MPa	3050 psi	ASTM D638-61T
Elongation at Break	30 %	30 %	ASTM D638-61T
Izod Impact, Notched	4.43 J/cm	8.30 ft-lb/in	ASTM D256-56
	0.800 J/cm	1.50 ft-lb/in	ASTM D256
	@Temperature -40.0 °C	@Temperature -40.0 °F	

Thermal Properties	Metric	English	Comments
Melting Point	139 °C	282 °F	Flow temperature, ASTM D569-59
Deflection Temperature at 0.46 MPa (66 psi)	77.0 °C	171 °F	ASTM D648-56

Electrical Properties	Metric	English	Comments
Dielectric Constant	3.43	3.43	ASTM D150-54T
	@Frequency 10000 Hz	@Frequency 10000 Hz	
	3.46	3.46	ASTM D150-54T
	@Frequency 1000 Hz	@Frequency 1000 Hz	
Dissipation Factor	0.0043	0.0043	ASTM D150-54T
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	0.0205	0.0205	ASTM D150-54T
	@Frequency 10000 Hz	@Frequency 10000 Hz	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China