

SABIC Innovative Plastics Cycology® C2950 PC+ABS (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Non-chlorinated and non-brominated flame retardant PC/ABS offering balanced flow and impact plus improved heat resistance intended for various applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycology-C2950-PCABS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
	1.22 g/cc	1.22 g/cc	color; ASTM D792
Water Absorption	0.10 %	0.10 %	ASTM D570
	@Time 86400 sec	@Time 24.0 hour	
Moisture Absorption at Equilibrium	0.40 %	0.40 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Linear Mold Shrinkage, Transverse	0.0040 - 0.0060 cm/cm	0.0040 - 0.0060 in/in	SABIC Method
	@Thickness 3.20 mm	@Thickness 0.126 in	
Melt Flow	10 g/10 min	10 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 260 °C	@Load 4.76 lb, Temperature 500 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	123	123	ASTM D785
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	40 %	40 %	Type I, 50 mm/min; ASTM D638
Flexural Yield Strength	102 MPa	14800 psi	2.6 mm/min, 100 mm span; ASTM D790
Flexural Modulus	2.65 GPa	384 ksi	2.6 mm/min, 100 mm span; ASTM D790
Izod Impact, Notched	5.34 J/cm	10.0 ft-lb/in	ASTM D256
	1.60 J/cm	3.00 ft-lb/in	ASTM D256
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	54.0 J	39.8 ft-lb	

Dart Drop, Total Energy Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	ASTM D3763 Comments
	61.0 J	45.0 ft-lb	ASTM D3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	72.0 µm/m-°C @Temperature -30.0 - 30.0 °C	40.0 µin/in-°F @Temperature -22.0 - 86.0 °F	ASTM D696
CTE, linear, Transverse to Flow	72.0 µm/m-°C @Temperature -30.0 - 30.0 °C	40.0 µin/in-°F @Temperature -22.0 - 86.0 °F	ASTM D696
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft²-°F	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	104 °C @Thickness 6.40 mm	219 °F @Thickness 0.252 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	90.0 °C @Thickness 3.20 mm	194 °F @Thickness 0.126 in	unannealed; ASTM D648
	95.0 °C @Thickness 6.40 mm	203 °F @Thickness 0.252 in	unannealed; ASTM D648
Vicat Softening Point	112 °C	234 °F	Rate B/50; ASTM D1525
UL RTI, Electrical	85.0 °C	185 °F	UL 746B
UL RTI, Mechanical with Impact	85.0 °C	185 °F	UL 746B
UL RTI, Mechanical without Impact	85.0 °C	185 °F	UL 746B
Flammability, UL94	V-0 @Thickness 1.49 mm	V-0 @Thickness 0.0587 in	UL 94
	5VB @Thickness 2.48 mm	5VB @Thickness 0.0976 in	UL 94
Oxygen Index	32 %	32 %	ASTM D2863

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+17 ohm-cm	1.00e+17 ohm-cm	ASTM D257
Surface Resistance	>= 1.00e+16 ohm	>= 1.00e+16 ohm	ASTM D257
	3.0	3.0	

Electrical Properties	Metric	English	Comments
	Hz	Hz	
	3.0	3.0	ASTM D150
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	19.4 kV/mm	493 kV/in	in oil; ASTM D149
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0049	0.0049	ASTM D150
	@Frequency 100 Hz	@Frequency 100 Hz	
	0.0050	0.0050	ASTM D150
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Arc Resistance	60 - 120 sec	60 - 120 sec	Tungsten; ASTM D495
Comparative Tracking Index	400 - 600 V	400 - 600 V	UL 746A
Hot Wire Ignition, HWI	60 - 120 sec	60 - 120 sec	UL 746A
High Amp Arc Ignition, HAI	>= 120 arcs	>= 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	25.4 - 80.0 mm/min	1.00 - 3.15 in/min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China