

SABIC Innovative Plastics Cycloy® C4210HF PC+ABS (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Glass Fiber Filled , Polycarbonate (PC)

Material Notes:

CYCOLOY C4210HF is a 10% glass reinforced, non-FR PC+ABS grade with high heat resistance, excellent strength and rigidity with good cosmetic appearance. It combines a good processability with a low shrinkage. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycloy-C4210HF-PCABS-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.22 g/cc	0.0441 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.20 %	0.20 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.60 % @Temperature 23.0 °C	0.60 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	on tensile bar; SABIC Method
Melt Flow	33 g/10 min @Load 5.00 kg, Temperature 260 °C	33 g/10 min @Load 11.0 lb, Temperature 500 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	121	121	ISO 2039-2
Hardness, H358/30	116 MPa	16800 psi	ISO 2039-1
Tensile Strength at Break	90.0 MPa	13100 psi	5 mm/min; ISO 527
Tensile Strength, Yield	90.0 MPa	13100 psi	5 mm/min; ISO 527
Elongation at Break	3.2 %	3.2 %	5 mm/min; ISO 527
Elongation at Yield	3.2 %	3.2 %	5 mm/min; ISO 527
Tensile Modulus	4.70 GPa	682 ksi	1 mm/min; ISO 527
Flexural Strength	135 MPa	19600 psi	2 mm/min; ISO 178
Flexural Yield Strength	125 MPa	18100 psi	2 mm/min; ISO 178
Flexural Modulus	4.25 GPa	616 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	8.00 kJ/m ²	3.81 ft-lb/in ²	80*10*3; ISO 180/1A

Mechanical Properties	@Temperature 23.0 °C Metric	@Temperature 73.4 °F English	Comments
Izod Impact, Unnotched (ISO)	20.0 kJ/m ² @Temperature 23.0 °C	9.52 ft-lb/in ² @Temperature 73.4 °F	80*10*3; ISO 180/1U
Charpy Impact Unnotched	2.00 J/cm ² @Temperature 23.0 °C	9.52 ft-lb/in ² @Temperature 73.4 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eU
Charpy Impact, Notched	0.800 J/cm ² @Temperature 23.0 °C	3.81 ft-lb/in ² @Temperature 73.4 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	40.0 µm/m-°C @Temperature -40.0 - 40.0 °C	22.2 µin/in-°F @Temperature -40.0 - 104 °F	ISO 11359-2
CTE, linear, Transverse to Flow	80.0 µm/m-°C @Temperature -40.0 - 40.0 °C	44.4 µin/in-°F @Temperature -40.0 - 104 °F	ISO 11359-2
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	133 °C	271 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	123 °C	253 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	134 °C	273 °F	Rate B/50; ISO 306
	136 °C	277 °F	Rate B/120; ISO 306
UL RTI, Electrical	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical with Impact	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical without Impact	60.0 °C	140 °F	UL 746B

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	IEC 60093
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ROA; IEC 60093

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2
Ball Pressure Test, 75°C +/- 2°C	PASSES	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China