

SABIC Innovative Plastics Cycloy® CX5430 PC+ABS (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Cycloy* resin CX5430 is a general purpose PC/ABS blend developed for thin wall applications requiring weld line strength, high flow and impact together with a good balance of other properties. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycloy-CX5430-PCABS-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.15 g/cc	1.15 g/cc	ASTM D 792
Density	1.15 g/cc	0.0415 lb/in ³	molded; ISO 1183
	1.15 g/cc	0.0415 lb/in ³	ISO 1183
Moisture Absorption at Equilibrium	0.070 %	0.070 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.30 % @Temperature 23.0 °C	0.30 % @Temperature 73.4 °F	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm @Thickness 3.20 mm	0.0050 - 0.0070 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	18 g/10 min @Load 5.00 kg, Temperature 260 °C	18 g/10 min @Load 11.0 lb, Temperature 500 °F	[cm ³ /10 min] Melt Volume Rate; ISO 1133
	19 g/10 min @Load 5.00 kg, Temperature 260 °C	19 g/10 min @Load 11.0 lb, Temperature 500 °F	ASTM D 1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	90	90	ISO 2039-2
Hardness, Rockwell R	115	115	ISO 2039-2
Tensile Strength at Break	44.0 MPa	6380 psi	5 mm/min; ISO 527
	44.0 MPa	6380 psi	50 mm/min; ISO 527
	45.0 MPa	6530 psi	Type I, 50 mm/min; ASTM D 638
Tensile Strength, Yield	44.0 MPa	6380 psi	5 mm/min; ISO 527
	48.0 MPa	6960 psi	50 mm/min; ISO 527

Mechanical Properties	Metric	English	Comments
	MPa	ksi	5 mm/min; ASTM D 638
Elongation at Break	>= 50 %	>= 50 %	Type I, 50 mm/min; ASTM D 638
	>= 50 %	>= 50 %	5 mm/min; ISO 527
	>= 50 %	>= 50 %	50 mm/min; ISO 527
Elongation at Yield	5.0 %	5.0 %	Type I, 50 mm/min; ASTM D 638
	5.0 %	5.0 %	5 mm/min; ISO 527
	5.0 %	5.0 %	50 mm/min; ISO 527
Tensile Modulus	2.40 GPa	348 ksi	5 mm/min; ASTM D 638
	2.40 GPa	348 ksi	1 mm/min; ISO 527
Flexural Yield Strength	75.0 MPa	10900 psi	2 mm/min; ISO 178
	75.0 MPa	10900 psi	1.3 mm/min, 50 mm span; ASTM D 790
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
	2.30 GPa	334 ksi	1.3 mm/min, 50 mm span; ASTM D 790
Izod Impact, Notched	1.10 J/cm @Temperature 23.0 °C	2.06 ft-lb/in @Temperature 73.4 °F	double-gated; SABIC Method
	2.50 J/cm @Temperature -30.0 °C	4.68 ft-lb/in @Temperature -22.0 °F	ASTM D 256
	5.00 J/cm @Temperature 23.0 °C	9.37 ft-lb/in @Temperature 73.4 °F	ASTM D 256
Izod Impact, Notched (ISO)	20.0 kJ/m² @Temperature -30.0 °C	9.52 ft-lb/in² @Temperature -22.0 °F	80*10*3; ISO 180/1A
	40.0 kJ/m² @Temperature 23.0 °C	19.0 ft-lb/in² @Temperature 73.4 °F	80*10*3; ISO 180/1A
Charpy Impact, Notched	2.00 J/cm² @Temperature -30.0 °C	9.52 ft-lb/in² @Temperature -22.0 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
	4.00 J/cm² @Temperature 23.0 °C	19.0 ft-lb/in² @Temperature 73.4 °F	V-notch Edgew 80*10*3 sp=62mm; ISO 179/1eA
Impact Test	80.0 J	59.0 ft-lb	Multiaxial Impact; ISO 6603

Mechanical Properties	40.0 J Metric	29.5 ft-lb English	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature -30.0 °C	@Temperature -22.0 °F	
	55.0 J	40.6 ft-lb	Instrumented Impact Total Energy; ASTM D 3763
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Taber Abrasion, mg/1000 Cycles	70	70	CS-17; SABIC Method
	@Load 1.00 kg	@Load 2.20 lb	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	80.0 µm/m-°C	44.4 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	80.0 µm/m-°C	44.4 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft²-°F	ISO 8302
	0.200 W/m-K	1.39 BTU-in/hr-ft²-°F	ASTM C 177
Hot Ball Pressure Test	<= 100 °C	<= 212 °F	IEC 60695-10-2
Deflection Temperature at 0.46 MPa (66 psi)	117 °C	243 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
	115 °C	239 °F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	95.0 °C	203 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	95.0 °C	203 °F	unannealed; ASTM D 648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Vicat Softening Point	114 °C	237 °F	Rate B/50; ISO 306
	115 °C	239 °F	Rate B/120; ISO 306
	115 °C	239 °F	Rate B/50; ASTM D 1525

UL RTI Electrical Thermal Properties	60.0 °C Metric	140 °F English	UL 746B Comments
UL RTI, Mechanical with Impact	60.0 °C	140 °F	UL 746B
UL RTI, Mechanical without Impact	60.0 °C	140 °F	UL 746B
Flammability, UL94	HB	HB	UL 94
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	HB	HB	2nd value; UL 94
	@Thickness 3.00 mm	@Thickness 0.118 in	
Glow Wire Test	650 °C	1200 °F	Glow Wire Flammability Index; IEC 60695-2-12
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Volume Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	ASTM D 257
Surface Resistance	>= 1.00e+15 ohm	>= 1.00e+15 ohm	ASTM D 257
Dielectric Constant	2.7	2.7	IEC 60250
	@Frequency 1000 Hz	@Frequency 1000 Hz	
	2.9	2.9	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	25.0 kV/mm	635 kV/in	in oil; IEC 60243-1
	@Thickness 1.50 mm	@Thickness 0.0591 in	
	35.0 kV/mm	889 kV/in	in oil; IEC 60243-1
	@Thickness 0.800 mm	@Thickness 0.0315 in	
Dissipation Factor	0.010	0.010	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.011	0.011	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	

Descriptive Properties	Value	Comments
Ball Pressure Test, 75°C +/- 2°C	pass	IEC 60695-10-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China