

SABIC Innovative Plastics Cycology® MC8100 PC+ABS (Asia Pacific)

Category : Polymer , Thermoplastic , ABS Polymer , Polycarbonate/ABS Alloy, Unreinforced , Polycarbonate (PC)

Material Notes:

Extrusion blowmolding grade.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Cycology-MC8100-PCABS-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
Water Absorption	0.10 % @Time 86400 sec	0.10 % @Time 24.0 hour	ASTM D570
Moisture Absorption at Equilibrium	0.40 %	0.40 %	ASTM D570
Linear Mold Shrinkage, Flow	0.0040 - 0.0070 cm/cm @Thickness 3.20 mm	0.0040 - 0.0070 in/in @Thickness 0.126 in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	52.0 MPa	7540 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	100 %	100 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	5.0 %	5.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.06 GPa	299 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	77.0 MPa	11200 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.06 GPa	299 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	5.34 J/cm	10.0 ft-lb/in	ASTM D256
	4.27 J/cm @Temperature -30.0 °C	8.00 ft-lb/in @Temperature -22.0 °F	ASTM D256
Dart Drop, Total Energy	47.0 J @Temperature -30.0 °C	34.7 ft-lb @Temperature -22.0 °F	ASTM D3763
	54.0 J @Temperature 23.0 °C	39.8 ft-lb @Temperature 73.4 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties CTE, linear, Parallel to Flow	81.0 $\mu\text{m}/\text{m}\cdot^\circ\text{C}$ Metric	45.0 $\mu\text{in}/\text{in}\cdot^\circ\text{F}$ English	Comments ASTM E 831
	@Temperature -40.0 - 40.0 $^\circ\text{C}$	@Temperature -40.0 - 104 $^\circ\text{F}$	
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² - $^\circ\text{F}$	ASTM C177
Deflection Temperature at 0.46 MPa (66 psi)	123 $^\circ\text{C}$ @Thickness 3.20 mm	253 $^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	104 $^\circ\text{C}$ @Thickness 3.20 mm	219 $^\circ\text{F}$ @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China