

SABIC Innovative Plastics LNP COLORCOMP D1000P PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Colorcomp* D1000P is a compound based on Polycarbonate resin containing Unfilled Custom Color. Added features of this material include: Exceptional Processing.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-COLORCOMP-D1000P-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183
	1.20 g/cc	0.0434 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0065 cm/cm	0.0065 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0075 cm/cm	0.0075 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.0070 - 0.0090 cm/cm	0.0070 - 0.0090 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	56.0 MPa	8120 psi	ASTM D638
	59.0 MPa	8560 psi	ISO 527
Tensile Strength, Yield	62.0 MPa	8990 psi	ASTM D638
	64.0 MPa	9280 psi	ISO 527
Elongation at Break	78.7 %	78.7 %	ASTM D638
	87 %	87 %	ISO 527
Elongation at Yield	5.3 %	5.3 %	ASTM D638
	5.6 %	5.6 %	ISO 527
Tensile Modulus	2.06 GPa	299 ksi	50 mm/min; ASTM D638
	2.21 GPa	321 ksi	1 mm/min; ISO 527

Flexural Strength Mechanical Properties	81.0 MPa Metric	11700 psi English	ISO 178 Comments
Flexural Modulus	2.30 GPa	334 ksi	ISO 178
	2.75 GPa	399 ksi	ASTM D790
Izod Impact, Notched	5.44 J/cm	10.2 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	13.0 kJ/m ²	6.19 ft-lb/in ²	80*10*4; ISO 180/1A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	124 °C	255 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	123 °C @Thickness 3.20 mm	253 °F @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China