

SABIC Innovative Plastics LNP LUBRICOMP DFL36G PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Lubricomp* DFL36G is a compound based on Polycarbonate resin containing Glass Fiber, PTFE, Milled Glass. Added features of this material include: Internally Lubricated.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-DFL36G-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.54 g/cc	0.0556 lb/in ³	ISO 1183
	1.55 g/cc	0.0560 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0024 cm/cm	0.0024 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0030 - 0.0050 cm/cm	0.0030 - 0.0050 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0043 cm/cm	0.0043 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	86.0 MPa	12500 psi	ASTM D638
	90.0 MPa	13100 psi	ISO 527
Tensile Strength, Yield	90.0 MPa	13100 psi	ISO 527
	91.0 MPa	13200 psi	ASTM D638
Elongation at Break	2.3 %	2.3 %	ISO 527
	2.4 %	2.4 %	ASTM D638
Elongation at Yield	2.3 %	2.3 %	ASTM D638
	2.3 %	2.3 %	ISO 527
Tensile Modulus	7.28 GPa	1060 ksi	1 mm/min; ISO 527
	7.58 GPa	1100 ksi	50 mm/min; ASTM D638

Flexural Strength Mechanical Properties	137 MPa Metric	19900 psi English	ASTM D790 Comments
Flexural Modulus	6.89 GPa	999 ksi	ASTM D790
	7.00 GPa	1020 ksi	ISO 178
Izod Impact, Notched	5.66 J/cm	10.6 ft-lb/in	ASTM D256
Izod Impact, Unnotched	1.33 J/cm	2.49 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	12.0 kJ/m ²	5.71 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	37.0 kJ/m ²	17.6 ft-lb/in ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	18.0 J	13.3 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	5.00 J	3.69 ft-lb	Multiaxial Impact; ISO 6603
Coefficient of Friction, Dynamic	0.49	0.49	ASTM D3702 Modified
Coefficient of Friction, Static	0.41	0.41	ASTM D3702 Modified
K (wear) Factor	82.6 x 10 ⁻⁸ mm ³ /N-M	41.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	Washer; ASTM D3702 Modified

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	57.6 µm/m-°C	32.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	58.0 µm/m-°C	32.2 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
CTE, linear, Transverse to Flow	28.0 µm/m-°C	15.6 µin/in-°F	ISO 11359-2
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
	28.8 µm/m-°C	16.0 µin/in-°F	ASTM E 831
	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	
Deflection Temperature at 0.46 MPa (66 psi)	144 °C	291 °F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	143 °C	289 °F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	140 °C	284 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	138 °C	280 °F	

Thermal Properties	Metric @ Thickness 3.20 mm	English @ Thickness 0.126 in	unannealed; ASTM D648 Comments
--------------------	-------------------------------	---------------------------------	-----------------------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China