

SABIC Innovative Plastics LNP LUBRICOMP RFL16 PA 66 (Asia Pacific)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

LNP LUBRICOMP* RFL16 is a compound based on Nylon 66 resin containing Glass Fiber, PTFE. Added features of this material include:
Internally Lubricated.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-LUBRICOMP-RFL16-PA-66-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.43 g/cc	0.0517 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	183 MPa	26500 psi	ASTM D638
Elongation at Break	3.2 %	3.2 %	ASTM D638
Flexural Strength	270 MPa	39200 psi	ASTM D790
Flexural Modulus	9.30 GPa	1350 ksi	ASTM D790
Izod Impact, Notched	1.12 J/cm	2.10 ft-lb/in	ASTM D256
Izod Impact, Unnotched	10.68 J/cm	20.01 ft-lb/in	ASTM D4812
Coefficient of Friction, Dynamic	0.62	0.62	ASTM D3702 Modified
Coefficient of Friction, Static	0.52	0.52	ASTM D3702 Modified
K (wear) Factor	24.2 x 10 ⁻⁸ mm ³ /N-M	12.0 x 10 ⁻¹⁰ in ³ -min/ft-lb-hr	Washer; ASTM D3702 Modified

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	254 Â°C @Thickness 3.20 mm	489 Â°F @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China