

SABIC Innovative Plastics LNP Lubricomp UFL36ASP PPA (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyphthalamide (PPA)

Material Notes:

LNP* LUBRICOMP* UFL36ASP is a compound based on Polyphthalamide resin containing Glass Fiber, PTFE. Added features include Internally Lubricated, Heat Stabilized. This data was supplied by SABIC-IP for the Europe-Africa-Middle East region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-Lubricomp-UFL36ASP-PPA-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.54 g/cc	0.0556 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm	0.0020 - 0.0040 in/in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	190 MPa	27600 psi	5 mm/min; ISO 527
Elongation at Break	2.1 %	2.1 %	5 mm/min; ISO 527
Tensile Modulus	10.6 GPa	1540 ksi	1 mm/min; ISO 527
Flexural Yield Strength	250 MPa	36300 psi	2 mm/min; ISO 178
Flexural Modulus	9.90 GPa	1440 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	11.0 kJ/m ² @Temperature 23.0 Â°C	5.23 ft-lb/in ² @Temperature 73.4 Â°F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	45.0 kJ/m ² @Temperature 23.0 Â°C	21.4 ft-lb/in ² @Temperature 73.4 Â°F	80*10*4; ISO 180/1U
Coefficient of Friction, Dynamic	0.48	0.48	ASTM D 3702 Modified
Coefficient of Friction, Static	0.52	0.52	ASTM D 3702 Modified
K (wear) Factor	10.1 x 10 ⁻⁸ mm ³ /N-M	5.00 x 10 ⁻¹⁰ in ³ - min/ft-lb-hr	Washer; ASTM D 3702 Modified

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	22.0 Âµm/m-Â°C @Temperature 23.0 - 60.0 Â°C	12.2 Âµin/in-Â°F @Temperature 73.4 - 140 Â°F	ISO 11359-2
	58.0 Âµm/m-Â°C	32.2 Âµin/in-Â°F	

Thermal Properties	Metric	English	Comments
Heat Deflection Temperature to Flow	@ Temperature 23.0 - 60.0 Â°C	@ Temperature 73.4 - 140 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	280 Â°C	536 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China