

SABIC Innovative Plastics LNP STAT-KON 9X06519 Cyclic Olefinic Copolymer (Asia Pacific)

Category : Polymer , Thermoplastic , Cyclo Olefin Polymer

Material Notes:

LNP STAT-KON* 9X06519 is a compound based on Cyclic Olefinic Copolymer resin containing Carbon Fiber. Added features of this material include: Clean Compounding System.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-9X06519-Cyclic-Olefinic-Copolymer-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.17 g/cc	0.0423 lb/in ³	ASTM D792

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	74.0 MPa	10700 psi	ASTM D638
Elongation at Break	0.50 %	0.50 %	ASTM D638
Tensile Modulus	16.04 GPa	2326 ksi	50 mm/min; ASTM D638
Flexural Strength	158 MPa	22900 psi	ASTM D790
Flexural Modulus	16.68 GPa	2419 ksi	ASTM D790
Izod Impact, Notched	0.320 J/cm	0.599 ft-lb/in	ASTM D256
Izod Impact, Unnotched	1.22 J/cm	2.29 ft-lb/in	ASTM D4812

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	2.80 Åµm/m-Å°C	1.56 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	12.6 Åµm/m-Å°C	7.00 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	150 Å°C	302 Å°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Surface Resistance	10 ohm - 1e+05	10 ohm - 1e+05	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China