

SABIC Innovative Plastics LNP STAT-KON TD000 PU

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

LNP* STAT-KON* TD000 is an unfilled compound based on Polyurethane resin. Added feature of this material is: Electrically Conductive.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-STAT-KON-TD000-PU.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.26 g/cc	1.26 g/cc	ASTM D792
Density	1.26 g/cc	0.0455 lb/in ³	ASTM D792
Moisture Absorption	0.500 %	0.500 %	50% RH, 24 hrs; ASTM D570
	0.790 %	0.790 %	23°C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	>= 0.020 cm/cm @Time 86400 sec	>= 0.020 in/in @Time 24.0 hour	ASTM D955
Linear Mold Shrinkage, Transverse	0.010 - 0.030 cm/cm @Time 86400 sec	0.010 - 0.030 in/in @Time 24.0 hour	ASTM D955

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	24.0 MPa	3480 psi	5 mm/min; ISO 527
	25.0 MPa	3630 psi	ASTM D638
Tensile Strength, Yield	24.0 MPa	3480 psi	5 mm/min; ISO 527
	26.0 MPa	3770 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	140 %	140 %	5 mm/min; ISO 527
	160 %	160 %	ASTM D638
Elongation at Yield	140 %	140 %	5 mm/min; ISO 527
	160 %	160 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	0.180 GPa	26.1 ksi	50 mm/min; ASTM D638
	0.300 GPa	43.5 ksi	1 mm/min; ISO 527
Flexural Strength	6.00 MPa	870 psi	ASTM D790
	16.0 MPa	2320 psi	ISO 178
Flexural Modulus	0.350 GPa	50.8 ksi	2 mm/min; ISO 178

Mechanical Properties	Metric 0.300 GPa	English 52.4 ksi	Comments ASTM D790
Izod Impact, Notched	7.94 J/cm	14.9 ft-lb/in	ASTM D256
Izod Impact, Unnotched	10.03 J/cm	18.79 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	78.0 kJ/mÂ²	37.1 ft-lb/inÂ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	87.0 kJ/mÂ²	41.4 ft-lb/inÂ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	50.0 J @Temperature 23.0 Â°C	36.9 ft-lb @Temperature 73.4 Â°F	ASTM D3763
Impact Test	55.0 J	40.6 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	12.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	6.67 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	ASTM D696
CTE, linear, Transverse to Flow	14.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	7.78 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	69.0 Â°C	156 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	70.0 Â°C @Thickness 3.20 mm	158 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	48.0 Â°C	118 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	47.0 Â°C @Thickness 3.20 mm	117 Â°F @Thickness 0.126 in	unannealed; ASTM D648

Electrical Properties	Metric	English	Comments
Surface Resistance	10000 - 1.00e+6 ohm	10000 - 1.00e+6 ohm	ASTM D257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China