

SABIC Innovative Plastics LNP Stat-kon MD000IU PP (Asia Pacific)

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

LNP* Stat-kon* MD000IU is a compound based on Polypropylene resin containing Carbon Powder. Added features of this material include: Electrically Conductive, High Impact, UV Stabilized. This data was supplied by SABIC-IP for the Asia Pacific region.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-Stat-kon-MD000IU-PP-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	0.970 g/cc	0.0350 lb/in ³	ISO 1183
	0.980 g/cc	0.0354 lb/in ³	ASTM D 792
Linear Mold Shrinkage, Flow	0.016 - 0.018 cm/cm	0.016 - 0.018 in/in	ASTM D 955
	@Time 86400 sec	@Time 24.0 hour	
	0.016 - 0.018 cm/cm	0.016 - 0.018 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.016 - 0.018 cm/cm	0.016 - 0.018 in/in	ASTM D 955
	@Time 86400 sec	@Time 24.0 hour	
	0.016 - 0.018 cm/cm	0.016 - 0.018 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	16.0 MPa	2320 psi	ASTM D 638
	17.0 MPa	2470 psi	ISO 527
Tensile Strength, Yield	18.0 MPa	2610 psi	ISO 527
	21.0 MPa	3050 psi	ASTM D 638
Elongation at Break	133.8 %	133.8 %	ASTM D 638
Elongation at Yield	9.0 %	9.0 %	ASTM D 638
Tensile Modulus	0.480 GPa	69.6 ksi	50 mm/min; ASTM D 638
	1.10 GPa	160 ksi	1 mm/min; ISO 527
Flexural Strength	20.0 MPa	2900 psi	ASTM D 790
	27.0 MPa	3920 psi	ISO 178

Flexural Modulus Mechanical Properties	1.13 GPa Metric	164 ksi English	ASTM D 790 Comments
	1.20 GPa	174 ksi	ISO 178
Izod Impact, Notched	8.33 J/cm @Temperature 23.0 °C	15.6 ft-lb/in @Temperature 73.4 °F	ASTM D 256
Izod Impact, Unnotched	15.48 J/cm @Temperature 23.0 °C	29.00 ft-lb/in @Temperature 73.4 °F	ASTM D 4812
Izod Impact, Notched (ISO)	65.0 kJ/m² @Temperature 23.0 °C	30.9 ft-lb/in² @Temperature 73.4 °F	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	112 kJ/m² @Temperature 23.0 °C	53.3 ft-lb/in² @Temperature 73.4 °F	80*10*4; ISO 180/1U
Impact Test	31.0 J	22.9 ft-lb	Multiaxial Impact; ISO 6603
	24.0 J @Temperature 23.0 °C	17.7 ft-lb @Temperature 73.4 °F	Instrumented Impact Energy @ peak; ASTM D 3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	101 µm/m-°C @Temperature -40.0 - 40.0 °C	56.1 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
	101 µm/m-°C @Temperature -40.0 - 40.0 °C	56.1 µin/in-°F @Temperature -40.0 - 104 °F	ISO 11359-2
CTE, linear, Transverse to Flow	119 µm/m-°C @Temperature -40.0 - 40.0 °C	66.1 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
	119 µm/m-°C @Temperature -40.0 - 40.0 °C	66.1 µin/in-°F @Temperature -40.0 - 104 °F	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	81.0 °C @Thickness 3.20 mm	178 °F @Thickness 0.126 in	unannealed; ASTM D 648
Deflection Temperature at 1.8 MPa (264 psi)	56.0 °C	133 °F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	52.0 °C @Thickness 3.20 mm	126 °F @Thickness 0.126 in	unannealed; ASTM D 648

Electrical Properties	Metric	English	Comments
Surface Resistance	10 - 1.00e+6 ohm	10 - 1.00e+6 ohm	ASTM D 257

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China