

SABIC Innovative Plastics LNP THERMOCOMP AX02749 ABS

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

LNP* THERMOCOMP* AX02749 is a compound based on ABS containing proprietary fillers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-AX02749-ABS.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183
Moisture Absorption	0.250 %	0.250 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	76.0 MPa	11000 psi	Type I, 5 mm/min; ASTM D638
	77.0 MPa	11200 psi	5 mm/min; ISO 527
Elongation at Break	1.8 %	1.8 %	5 mm/min; ISO 527
	2.0 %	2.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	6.04 GPa	876 ksi	1 mm/min; ISO 527
	6.08 GPa	882 ksi	50 mm/min; ASTM D638
Flexural Strength	119 MPa	17300 psi	ISO 178
	122 MPa	17700 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	5.97 GPa	866 ksi	2 mm/min; ISO 178
	6.08 GPa	882 ksi	1.3 mm/min, 50 mm span; ASTM

Mechanical Properties	Metric	English	0790 Comments
Izod Impact, Notched	0.800 J/cm	1.50 ft-lb/in	ASTM D256
Izod Impact, Unnotched	3.74 J/cm	7.01 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	7.00 kJ/m ²	3.33 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	23.0 kJ/m ²	10.9 ft-lb/in ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	13.0 J @Temperature 23.0 Â°C	9.59 ft-lb @Temperature 73.4 Â°F	ASTM D3763
Impact Test	2.00 J	1.48 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	56.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	31.1 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	ASTM D696
CTE, linear, Transverse to Flow	52.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	28.9 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	ASTM D696
Deflection Temperature at 1.8 MPa (264 psi)	100 Â°C	212 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	100 Â°C @Thickness 3.20 mm	212 Â°F @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China