

SABIC Innovative Plastics LNP THERMOCOMP DB0049R PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Thermocomp* DB0049R is a compound based on Polycarbonate resin containing Glass Bead, Flame Retardant. Added features of this material include: Flame Retardant.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-DB0049R-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.37 g/cc	0.0495 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	50.0 MPa	7250 psi	5 mm/min; ISO 527
Elongation at Yield	4.8 %	4.8 %	5 mm/min; ISO 527
Tensile Modulus	2.80 GPa	406 ksi	1 mm/min; ISO 527
Flexural Yield Strength	86.0 MPa	12500 psi	2 mm/min; ISO 178
Flexural Modulus	2.80 GPa	406 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	14.0 kJ/m ²	6.66 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	75.0 kJ/m ²	35.7 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	141 Â°C	286 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	129 Â°C	264 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	UL 94

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China