

**SABIC Innovative Plastics LNP THERMOCOMP DX06409 PC**

Category : Polymer , Thermoplastic , Polycarbonate (PC)

**Material Notes:**

LNP\* THERMOCOMP\* DX06409 is a compound based on Polycarbonate resin containing 20% Glass Fiber. Added features of this material include: Easy Molding, Mold Release, Healthcare.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_SABIC-Innovative-Plastics-LNP-THERMOCOMP-DX06409-PC.php](http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-DX06409-PC.php)

Physical Properties	Metric	English	Comments
Density	1.27 g/cc	0.0459 lb/in <sup>3</sup>	ISO 1183
	1.28 g/cc	0.0462 lb/in <sup>3</sup>	ASTM D792
Moisture Absorption	0.100 %	0.100 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0043 cm/cm	0.0043 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0050 cm/cm	0.0050 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0051 cm/cm	0.0051 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	83.0 MPa	12000 psi	ASTM D638
	84.0 MPa	12200 psi	ISO 527
Elongation at Break	3.6 %	3.6 %	ISO 527
	3.8 %	3.8 %	ASTM D638
Tensile Modulus	4.10 GPa	595 ksi	1 mm/min; ISO 527
	4.17 GPa	605 ksi	50 mm/min; ASTM D638
Flexural Strength	117 MPa	17000 psi	ISO 178
	144 MPa	20900 psi	ASTM D790
Flexural Modulus	3.92 GPa	569 ksi	ISO 178

Mechanical Properties	4.28 GPa Metric	621 ksi English	ASTM D790 Comments
Izod Impact, Notched	0.960 J/cm	1.80 ft-lb/in	ASTM D256
Izod Impact, Unnotched	9.07 J/cm	17.0 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	8.00 kJ/m <sup>2</sup>	3.81 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	61.0 kJ/m <sup>2</sup>	29.0 ft-lb/in <sup>2</sup>	80*10*4; ISO 180/1U
Dart Drop, Total Energy	13.0 J	9.59 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	9.00 J	6.64 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	37.8 Åµm/m-Å°C	21.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	38.2 Åµm/m-Å°C	21.2 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
CTE, linear, Transverse to Flow	53.5 Åµm/m-Å°C	29.7 Åµin/in-Å°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 0.46 MPa (66 psi)	54.0 Åµm/m-Å°C	30.0 Åµin/in-Å°F	ASTM E 831
	@Temperature -40.0 - 40.0 Å°C	@Temperature -40.0 - 104 Å°F	
Deflection Temperature at 1.8 MPa (264 psi)	141 Å°C	286 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	141 Å°C	286 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	137 Å°C	279 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	136 Å°C	277 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	@Thickness 3.20 mm	@Thickness 0.126 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China