

SABIC Innovative Plastics LNP THERMOCOMP EXTC8143 PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

LNP* Thermocomp* EXTC8143 is a compound based on Polycarbonate resin containing Glass Fiber, Flame Retardant. Added features of this material include: High modulus, good flatness, good ductility, Non-Brominated & Non-Chlorinated Flame Retardant.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-EXTC8143-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Density	1.42 g/cc	0.0513 lb/in ³	ASTM D792
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm @Time 86400 sec	0.0010 - 0.0030 in/in @Time 24.0 hour	ASTM D955
Linear Mold Shrinkage, Transverse	0.0010 - 0.0030 cm/cm @Time 86400 sec	0.0010 - 0.0030 in/in @Time 24.0 hour	ASTM D955
Melt Index of Compound	15 g/10 min @Load 2.16 kg, Temperature 300 °C	15 g/10 min @Load 4.76 lb, Temperature 572 °F	MVR [cm ³ /10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	120 MPa	17400 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	2.4 %	2.4 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	9.04 GPa	1310 ksi	5 mm/min; ASTM D638
Flexural Strength	179 MPa	26000 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	8.39 GPa	1220 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	1.44 J/cm	2.70 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.94 J/cm	9.25 ft-lb/in	ASTM D4812
Charpy Impact Unnotched	3.60 J/cm ²	17.1 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eU
Charpy Impact, Notched	1.30 J/cm ²	6.19 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eA
Dart Drop, Total Energy	24.0 J	17.7 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	¹¹⁵ °C	²³⁰ °F	Comments
Deflection Temperature at 1.8 MPa (264 psi)	@Thickness 3.20 mm	@Thickness 0.126 in	unannealed; ASTM D648
Flammability, UL94	V-0 @Thickness 0.800 mm	V-0 @Thickness 0.0315 in	UL 94

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China