

SABIC Innovative Plastics LNP THERMOCOMP JF006LZZ PES

Category : Polymer , Thermoplastic , Polyethersulfone (PES)

Material Notes:

LNP THERMOCOMP* JF006LZZ is a compound based on Polyethersulfone resin containing 30% Glass Fiber. Added features of this material include: Extrusion Grade, Low Extractable.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-JF006LZZ-PES.php

Physical Properties	Metric	English	Comments
Density	1.60 g/cc	0.0578 lb/in ³	ISO 1183
	1.613 g/cc	0.05827 lb/in ³	ASTM D792
Moisture Absorption	0.360 %	0.360 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0020 cm/cm	0.0020 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
	0.0025 cm/cm	0.0025 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0069 cm/cm	0.0069 in/in	ISO 294
	@Time 86400 sec	@Time 24.0 hour	
	0.0070 cm/cm	0.0070 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	99.0 MPa	14400 psi	ISO 527
	113 MPa	16400 psi	ASTM D638
Elongation at Break	1.4 %	1.4 %	ISO 527
	1.8 %	1.8 %	ASTM D638
Tensile Modulus	9.79 GPa	1420 ksi	50 mm/min; ASTM D638
	10.19 GPa	1478 ksi	1 mm/min; ISO 527
Flexural Strength	178 MPa	25800 psi	ASTM D790
	222 MPa	32200 psi	ISO 178
Flexural Modulus	9.23 GPa	1340 ksi	ASTM D790

Mechanical Properties	9.24 GPa Metric	1340 ksi English	ISO 178 Comments
Izod Impact, Notched	0.580 J/cm	1.09 ft-lb/in	ASTM D256
Izod Impact, Unnotched	4.32 J/cm	8.09 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	6.00 kJ/mÂ²	2.86 ft-lb/inÂ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	29.0 kJ/mÂ²	13.8 ft-lb/inÂ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	12.0 J	8.85 ft-lb	Instrumented Impact Energy @ peak; ASTM D3763
Impact Test	2.00 J	1.48 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	30.0 Âµm/m-Â°C	16.7 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	30.1 Âµm/m-Â°C	16.7 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
CTE, linear, Transverse to Flow	36.3 Âµm/m-Â°C	20.2 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	36.4 Âµm/m-Â°C	20.2 Âµin/in-Â°F	ISO 11359-2
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	217 Â°C	423 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	212 Â°C	414 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China