

SABIC Innovative Plastics LNP THERMOCOMP KFB41 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Acetal (POM)

Material Notes:

LNP* THERMOCOMP* KFB41 is a compound based on Acetal Copolymer resin containing Glass Fiber, Glass Bead.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-KFB41-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.58 g/cc	0.0571 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.014 cm/cm	0.014 in/in	SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	40.0 MPa	5800 psi	5 mm/min; ISO 527
Tensile Strength, Yield	41.0 MPa	5950 psi	5 mm/min; ISO 527
Elongation at Yield	6.4 %	6.4 %	5 mm/min; ISO 527
Tensile Modulus	3.70 GPa	537 ksi	1 mm/min; ISO 527
Flexural Yield Strength	72.0 MPa	10400 psi	2 mm/min; ISO 178
Flexural Modulus	3.60 GPa	522 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	25.0 kJ/m ²	11.9 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	86.0 Âµm/m-Â°C	47.8 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
CTE, linear, Transverse to Flow	107 Âµm/m-Â°C	59.4 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	113 Â°C	235 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China