

SABIC Innovative Plastics LNP THERMOCOMP M7002XXH PP

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

LNP* THERMOCOMP* M7002XXH is a compound based on Polypropylene resin containing proprietary antimicrobial additives. Designed for touch surfaces in healthcare applications. Added features include: low antimicrobial performance, high mechanical strength, healthcare.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-M7002XXH-PP.php

Physical Properties	Metric	English	Comments
Density	1.00 g/cc	0.0361 lb/in ³	ASTM D792
Moisture Absorption	0.0100 %	0.0100 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0050 cm/cm	0.0050 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0070 cm/cm	0.0070 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Melt Flow	34 g/10 min	34 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 Â°C	@Load 4.76 lb, Temperature 446 Â°F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	36.0 MPa	5220 psi	5 mm/min; ISO 527
	38.0 MPa	5510 psi	Type I, 5 mm/min; ASTM D638
Tensile Modulus	1.80 GPa	261 ksi	1 mm/min; ISO 527
	1.85 GPa	268 ksi	5 mm/min; ASTM D638
Flexural Strength	35.0 MPa	5080 psi	ISO 178
Flexural Yield Strength	40.0 MPa	5800 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	1.25 GPa	181 ksi	2 mm/min; ISO 178
	1.40 GPa	203 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	0.280 J/cm	0.525 ft-lb/in	ASTM D256
Izod Impact, Notched (ISO)	2.00 kJ/mÂ²	0.952 ft-lb/inÂ²	80*10*4; ISO 180/1A

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 Â°C	230 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	115 Â°C	239 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China