

SABIC Innovative Plastics LNP THERMOCOMP MB006S PP (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

LNP* Thermocomp* MB006S is a compound based on Polypropylene resin containing Glass Bead. Added features of this material include:
Heat Stabilized.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-MB006S-PP-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.12 g/cc	0.0405 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.012 - 0.016 cm/cm	0.012 - 0.016 in/in	on Tensile Bar; SABIC Method

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	25.0 MPa	3630 psi	50 mm/min; ISO 527
Elongation at Yield	7.1 %	7.1 %	50 mm/min; ISO 527
Tensile Modulus	1.90 GPa	276 ksi	1 mm/min; ISO 527
Flexural Yield Strength	36.0 MPa	5220 psi	2 mm/min; ISO 178
Flexural Modulus	1.70 GPa	247 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	4.00 kJ/m ²	1.90 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	20.0 kJ/m ²	9.52 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	107 Âµm/m-Â°C	59.4 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
CTE, linear, Transverse to Flow	120 Âµm/m-Â°C	66.7 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
Deflection Temperature at 1.8 MPa (264 psi)	62.0 Â°C	144 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China