

SABIC Innovative Plastics LNP THERMOCOMP OCF62E PPS - Branched

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

LNP* THERMOCOMP* OCF62E is a compound based on PPS-Branched resin containing 10% Carbon Fiber, 30% Glass Fiber. Added feature of this material includes: Easy Molding

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-OCF62E-PPS-Branched.php

Physical Properties	Metric	English	Comments
Density	1.66 g/cc	0.0600 lb/in ³	ASTM D792
	1.66 g/cc	0.0600 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0010 - 0.0040 cm/cm	0.0010 - 0.0040 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0070 - 0.010 cm/cm	0.0070 - 0.010 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	133 MPa	19300 psi	5 mm/min; ISO 527
	157 MPa	22800 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	133 MPa	19300 psi	5 mm/min; ISO 527
	157 MPa	22800 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	0.50 %	0.50 %	5 mm/min; ISO 527
	0.70 %	0.70 %	Type I, 5 mm/min; ASTM D638
Elongation at Yield	0.50 %	0.50 %	5 mm/min; ISO 527
	0.70 %	0.70 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	28.6 GPa	4150 ksi	1 mm/min; ISO 527
	30.32 GPa	4398 ksi	50 mm/min; ASTM D638
Flexural Strength	206 MPa	29900 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Yield Strength	46.0 MPa	6670 psi	2 mm/min; ISO 178
	205 MPa	29700 psi	1.3 mm/min, 50 mm span; ASTM D790

Flexural Modulus Mechanical Properties	19.07 GPa Metric	2766 ksi English	1.3 mm/min, 50 mm span; ASTM D790 Comments
	20.56 GPa	2982 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.630 J/cm	1.18 ft-lb/in	ASTM D256
Izod Impact, Unnotched	2.60 J/cm	4.87 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	6.00 kJ/mÂ²	2.86 ft-lb/inÂ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	13.0 kJ/mÂ²	6.19 ft-lb/inÂ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	1.02 Âµm/m-Â°C	0.567 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
	1.02 Âµm/m-Â°C	0.567 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
CTE, linear, Transverse to Flow	4.57 Âµm/m-Â°C	2.54 Âµin/in-Â°F	ASTM E 831
	@Temperature -40.0 - 40.0 Â°C	@Temperature -40.0 - 104 Â°F	
	4.60 Âµm/m-Â°C	2.56 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	
Deflection Temperature at 0.46 MPa (66 psi)	281 Â°C	538 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	280 Â°C	536 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	
Deflection Temperature at 1.8 MPa (264 psi)	268 Â°C	514 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	267 Â°C	513 Â°F	unannealed; ASTM D648
	@Thickness 3.20 mm	@Thickness 0.126 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China