

SABIC Innovative Plastics LNP THERMOCOMP OF008 PPS - Linear (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polyphenylene Sulfide (PPS)

Material Notes:

LNP* Thermocomp* OF008 is a compound based on PPS - Linear resin containing Glass Fiber.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-OF008-PPS-Linear-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.65 g/cc	0.0596 lb/in ³	ISO 1183
Linear Mold Shrinkage, Flow	0.0020 - 0.0040 cm/cm @Time 86400 sec	0.0020 - 0.0040 in/in @Time 24.0 hour	ISO 294
Linear Mold Shrinkage, Transverse	0.0080 - 0.012 cm/cm @Time 86400 sec	0.0080 - 0.012 in/in @Time 24.0 hour	ISO 294

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	159 MPa	23100 psi	5 mm/min; ISO 527
Elongation at Break	1.4 %	1.4 %	5 mm/min; ISO 527
Tensile Modulus	14.4 GPa	2090 ksi	1 mm/min; ISO 527
Flexural Strength	233 MPa	33800 psi	2 mm/min; ISO 178
Flexural Modulus	12.9 GPa	1870 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	10.0 kJ/m ²	4.76 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	50.0 kJ/m ²	23.8 ft-lb/in ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	14.0 Åµm/m-Å°C @Temperature 23.0 - 60.0 Å°C	7.78 Åµin/in-Å°F @Temperature 73.4 - 140 Å°F	ISO 11359-2
CTE, linear, Transverse to Flow	45.0 Åµm/m-Å°C @Temperature 23.0 - 60.0 Å°C	25.0 Åµin/in-Å°F @Temperature 73.4 - 140 Å°F	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	278 Å°C	532 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
Deflection Temperature at 1.8 MPa (264 psi)	252 Å°C	486 Å°F	Flatw 80*10*4 sp=64mm; ISO 75/Af

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China