

SABIC Innovative Plastics LNP THERMOCOMP RC003SXS PA 66 (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

LNP* THERMOCOMP* RC003SXS is a compound based on PA 66 resin containing Carbon fiber. Added features include: Electrically Conductive, Heat Stabilized

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-RC003SXS-PA-66-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 1183
Water Absorption at Saturation	5.5 %	5.5 %	ISO 62
Linear Mold Shrinkage, Flow	0.0010 - 0.0020 cm/cm	0.0010 - 0.0020 in/in	on Tensile Bar; SABIC Method

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell L	105	105	ISO 2039-2
Tensile Strength at Break	170 MPa	24700 psi	5 mm/min; ISO 527
Elongation at Break	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	13.0 GPa	1890 ksi	1 mm/min; ISO 527
Flexural Strength	230 MPa	33400 psi	2 mm/min; ISO 178
Flexural Modulus	10.0 GPa	1450 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	5.00 kJ/m ²	2.38 ft-lb/in ²	80*10*4; ISO 180/1A
	3.00 kJ/m ²	1.43 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature -40.0 Â°C	@Temperature -40.0 Â°F	
	4.00 kJ/m ²	1.90 ft-lb/in ²	80*10*4; ISO 180/1A
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	
Charpy Impact Unnotched	4.50 J/cm ²	21.4 ft-lb/in ²	Edgew 80*10*4 sp=62mm; ISO 179/1eU

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	20.0 Âµm/m-Â°C	11.1 Âµin/in-Â°F	ISO 11359-2
	@Temperature 23.0 - 60.0 Â°C	@Temperature 73.4 - 140 Â°F	

Thermal Properties	Metric 110 Åµm/m-Å°C	English 51.7 Åµin/in-Å°F	Comments
CTE, linear, Transverse to Flow	@Temperature 23.0 - 60.0 Å°C	@Temperature 73.4 - 140 Å°F	ISO 11359-2
Deflection Temperature at 0.46 MPa (66 psi)	252 Å°C	486 Å°F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	250 Å°C	482 Å°F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	255 Å°C	491 Å°F	Rate B/120; ISO 306
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	UL 94 by SABIC-IP
Oxygen Index	28 %	28 %	ISO 4589

Electrical Properties	Metric	English	Comments
Volume Resistivity	178000 ohm-cm	178000 ohm-cm	IEC 60093
Surface Resistance	178000 ohm	178000 ohm	ROA; IEC 60093

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China