

SABIC Innovative Plastics LNP THERMOCOMP RF008S PA 66

Category : Polymer , Thermoplastic , Nylon , Nylon 66

Material Notes:

LNP* THERMOCOMP* RF008S is a compound based on Nylon 6/6 resin containing 40% Glass Fiber. Added features of this material include:
Heat Stabilized.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-RF008S-PA-66.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.48 g/cc	1.48 g/cc	ASTM D792
Density	1.48 g/cc	0.0535 lb/in ³	ISO 1183
Moisture Absorption	0.0600 %	0.0600 %	23 ^o C / 50% RH; ISO 62
	0.630 %	0.630 %	50% RH, 24 hrs; ASTM D570
Linear Mold Shrinkage, Flow	0.0010 - 0.0030 cm/cm	0.0010 - 0.0030 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0080 - 0.010 cm/cm	0.0080 - 0.010 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	213 MPa	30900 psi	Type I, 5 mm/min; ASTM D638
	214 MPa	31000 psi	5 mm/min; ISO 527
Elongation at Break	1.7 %	1.7 %	5 mm/min; ISO 527
	2.0 %	2.0 %	Type I, 5 mm/min; ASTM D638
Tensile Modulus	29.11 GPa	4222 ksi	50 mm/min; ASTM D638
	30.08 GPa	4363 ksi	1 mm/min; ISO 527
Flexural Strength	232 MPa	33600 psi	1.3 mm/min, 50 mm span; ASTM D790
	315 MPa	45700 psi	ISO 178
Flexural Modulus	6.27 GPa	909 ksi	1.3 mm/min, 50 mm span; ASTM D790
	13.02 GPa	1888 ksi	2 mm/min; ISO 178
Izod Impact, Notched	1.39 J/cm	2.60 ft-lb/in	ASTM D256

Izod Impact, Unnotched Mechanical Properties	14.55 J/cm Metric	27.25 ft-lb/in English	ASTM D4812 Comments
Izod Impact, Notched (ISO)	14.0 kJ/m ²	6.66 ft-lb/in ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	97.0 kJ/m ²	46.2 ft-lb/in ²	80*10*4; ISO 180/1U
Dart Drop, Total Energy	16.0 J @Temperature 23.0 Â°C	11.8 ft-lb @Temperature 73.4 Â°F	ASTM D3763
Impact Test	3.00 J	2.21 ft-lb	Multiaxial Impact; ISO 6603

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	24.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	13.3 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	ASTM D696
CTE, linear, Transverse to Flow	60.0 Âµm/m-Â°C @Temperature -30.0 - 30.0 Â°C	33.3 Âµin/in-Â°F @Temperature -22.0 - 86.0 Â°F	ASTM D696
Deflection Temperature at 0.46 MPa (66 psi)	258 Â°C	496 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	260 Â°C @Thickness 3.20 mm	500 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	249 Â°C	480 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	253 Â°C @Thickness 3.20 mm	487 Â°F @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China