

SABIC Innovative Plastics LNP THERMOCOMP WF007 PBT

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

LNP THERMOCOMP WF007 is a compound based on PBT resin containing 35% Glass Fiber.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-LNP-THERMOCOMP-WF007-PBT.php

Physical Properties	Metric	English	Comments
Density	1.60 g/cc	0.0578 lb/in ³	ASTM D792
	1.60 g/cc	0.0578 lb/in ³	ISO 1183
Moisture Absorption	0.0500 %	0.0500 %	50% RH, 24 hrs; ASTM D570
	0.0700 %	0.0700 %	23 ^o C / 50% RH; ISO 62
Linear Mold Shrinkage, Flow	0.0020 - 0.0050 cm/cm	0.0020 - 0.0050 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	
Linear Mold Shrinkage, Transverse	0.0090 - 0.020 cm/cm	0.0090 - 0.020 in/in	ASTM D955
	@Time 86400 sec	@Time 24.0 hour	

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	120 MPa	17400 psi	5 mm/min; ISO 527
	121 MPa	17500 psi	Type I, 5 mm/min; ASTM D638
Tensile Strength, Yield	120 MPa	17400 psi	5 mm/min; ISO 527
	121 MPa	17500 psi	Type I, 5 mm/min; ASTM D638
Elongation at Break	2.0 %	2.0 %	Type I, 5 mm/min; ASTM D638
	2.0 %	2.0 %	5 mm/min; ISO 527
Elongation at Yield	2.0 %	2.0 %	Type I, 5 mm/min; ASTM D638
	2.0 %	2.0 %	5 mm/min; ISO 527
Tensile Modulus	11.03 GPa	1600 ksi	1 mm/min; ISO 527
	16.88 GPa	2448 ksi	50 mm/min; ASTM D638
Flexural Strength	185 MPa	26800 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Yield Strength	185 MPa	26800 psi	1.3 mm/min, 50 mm span; ASTM D790

Mechanical Properties	185 MPa Metric	27000 psi English	2 mm/min; ISO 178 Comments
Flexural Modulus	9.83 GPa	1430 ksi	1.3 mm/min, 50 mm span; ASTM D790
	9.88 GPa	1430 ksi	2 mm/min; ISO 178
Izod Impact, Notched	0.780 J/cm	1.46 ft-lb/in	ASTM D256
Izod Impact, Unnotched	6.20 J/cm	11.6 ft-lb/in	ASTM D4812
Izod Impact, Notched (ISO)	7.00 kJ/mÂ²	3.33 ft-lb/inÂ²	80*10*4; ISO 180/1A
Izod Impact, Unnotched (ISO)	40.0 kJ/mÂ²	19.0 ft-lb/inÂ²	80*10*4; ISO 180/1U

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	222 Â°C	432 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Bf
	222 Â°C @Thickness 3.20 mm	432 Â°F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	203 Â°C	397 Â°F	Flatw 80*10*4 sp=64mm; ISO 75/Af
	207 Â°C @Thickness 3.20 mm	405 Â°F @Thickness 0.126 in	unannealed; ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China