

SABIC Innovative Plastics Lexan® 915R PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan® 915R Polycarbonate (PC) resin is a non-filled, injection moldable grade. This non-chlorinated, non-brominated flame retardant PC has a UL V0 rating with good flow and mold release properties. Lexan resin 915R is available in various opaque color options and is an excellent candidate for a wide variety of applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-915R-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm @Thickness 3.20 mm	0.0060 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	18 g/10 min @Load 1.20 kg, Temperature 300 °C	18 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	63.0 MPa	9140 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	130 %	130 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.40 GPa	348 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	93.0 MPa	13500 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.46 GPa	357 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	7.47 J/cm	14.0 ft-lb/in	ASTM D256
Dart Drop, Total Energy	67.0 J @Temperature 23.0 °C	49.4 ft-lb @Temperature 73.4 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	73.8 µm/m-°C @Temperature -40.0 - 40.0 °C	41.0 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	@Temperature -40.0 - 40.0 °C	@Temperature -40.0 - 104 °F	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	132 °C @Thickness 3.20 mm	270 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	123 °C @Thickness 3.20 mm	253 °F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	138 °C	280 °F	Rate B/50; ASTM D1525
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical with Impact	120 °C	248 °F	UL 746B
UL RTI, Mechanical without Impact	125 °C	257 °F	UL 746B
Flammability, UL94	V-0 @Thickness 1.09 mm	V-0 @Thickness 0.0429 in	UL 94
Glow Wire Test	800 °C	1470 °F	IEC 60695-2-13
	850 °C @Thickness 1.00 mm	1560 °F @Thickness 0.0394 in	IEC 60695-2-12
	960 °C @Thickness 1.60 mm	1760 °F @Thickness 0.0630 in	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	Tungsten; ASTM D495
Comparative Tracking Index	175 - 250 V	175 - 250 V	UL 746A
Hot Wire Ignition, HWI	30 - 60 sec	30 - 60 sec	UL 746A
High Amp Arc Ignition, HAI	60 - 120 arcs	60 - 120 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	0.000 - 10.0 mm/min	0.000 - 0.394 in/min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China