

SABIC Innovative Plastics Lexan® 945U PC (Europe-Africa-Middle East)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan® 945U Polycarbonate (PC) resin is a non-filled, injection moldable grade. This non-chlorinated, non-brominated flame retardant PC has an UL-94 V0 rating and is UV stabilized, providing additional weathering capability. Lexan 945U is available in various opaque color options and is a general-purpose resin ideal for a wide variety of applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-945U-PC-Europe-Africa-Middle-East.php

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in³	ISO 1183
Moisture Absorption	0.150 %	0.150 %	23°C / 50% RH; ISO 62
Water Absorption at Saturation	0.35 %	0.35 %	ISO 62
Linear Mold Shrinkage, Flow	0.0050 - 0.0070 cm/cm	0.0050 - 0.0070 in/in	on Tensile Bar; SABIC Method
Melt Index of Compound	10 g/10 min @Load 1.20 kg, Temperature 300 °C	10 g/10 min @Load 2.65 lb, Temperature 572 °F	MVR [cm³/10 min]; ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, H358/30	95.0 MPa	13800 psi	ISO 2039-1
Tensile Strength at Break	60.0 MPa	8700 psi	50 mm/min; ISO 527
Tensile Strength, Yield	63.0 MPa	9140 psi	50 mm/min; ISO 527
Elongation at Break	85 %	85 %	50 mm/min; ISO 527
Elongation at Yield	6.0 %	6.0 %	50 mm/min; ISO 527
Tensile Modulus	2.35 GPa	341 ksi	1 mm/min; ISO 527
Flexural Yield Strength	90.0 MPa	13100 psi	2 mm/min; ISO 178
Flexural Modulus	2.30 GPa	334 ksi	2 mm/min; ISO 178
Izod Impact, Notched (ISO)	70.0 kJ/m²	33.3 ft-lb/in²	80*10*3; ISO 180/1A
	12.0 kJ/m² @Temperature -30.0 °C	5.71 ft-lb/in² @Temperature -22.0 °F	80*10*3; ISO 180/1A
Izod Impact, Unnotched (ISO)	NB	NB	80*10*3; ISO 180/1U
	NB	NB	

Mechanical Properties	Metric @ Temperature -30.0 °C	English @ Temperature -22.0 °F	80*10*3- ISO 180/1U Comments
Charpy Impact Unnotched	NB	NB	Edgew 80*10*3 sp=62mm; ISO 179/1eU
	NB @Temperature -30.0 °C	NB @Temperature -22.0 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eU
Charpy Impact, Notched	7.30 J/cm ²	34.7 ft-lb/in ²	Edgew 80*10*3 sp=62mm; ISO 179/1eA
	1.40 J/cm ² @Temperature -30.0 °C	6.66 ft-lb/in ² @Temperature -22.0 °F	Edgew 80*10*3 sp=62mm; ISO 179/1eA

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	70.0 µm/m-°C @Temperature 23.0 - 80.0 °C	38.9 µin/in-°F @Temperature 73.4 - 176 °F	ISO 11359-2
CTE, linear, Transverse to Flow	70.0 µm/m-°C @Temperature 23.0 - 80.0 °C	38.9 µin/in-°F @Temperature 73.4 - 176 °F	ISO 11359-2
Thermal Conductivity	0.200 W/m-K	1.39 BTU-in/hr-ft ² -°F	ISO 8302
Deflection Temperature at 0.46 MPa (66 psi)	136 °C	277 °F	Edgew 120*10*4 sp=100mm; ISO 75/Be
Deflection Temperature at 1.8 MPa (264 psi)	125 °C	257 °F	Edgew 120*10*4 sp=100mm; ISO 75/Ae
Vicat Softening Point	141 °C	286 °F	Rate B/50; ISO 306
	142 °C	288 °F	Rate B/120; ISO 306
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical with Impact	120 °C	248 °F	UL 746B
UL RTI, Mechanical without Impact	125 °C	257 °F	UL 746B
Flammability, UL94	V-0 @Thickness 1.50 mm	V-0 @Thickness 0.0591 in	UL 94
Oxygen Index	35 %	35 %	ISO 4589
Glow Wire Test	800 °C	1470 °F	IEC 60695-2-13
	960 °C @Thickness 1.00 mm	1760 °F @Thickness 0.0394 in	IEC 60695-2-12

Electrical Properties	Metric	English	Comments
Volume Resistivity	$\geq 1.00\text{e}+15$ ohm-cm	$\geq 1.00\text{e}+15$ ohm-cm	IEC 60093
Surface Resistance	$\geq 1.00\text{e}+15$ ohm	$\geq 1.00\text{e}+15$ ohm	ROA; IEC 60093
Dielectric Constant	2.7	2.7	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
	2.7	2.7	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
Dielectric Strength	17.0 kV/mm	432 kV/in	in oil; IEC 60243-1
	@Thickness 3.20 mm	@Thickness 0.126 in	
Dissipation Factor	0.0010	0.0010	IEC 60250
	@Frequency 50.0 - 60.0 Hz	@Frequency 50.0 - 60.0 Hz	
	0.010	0.010	IEC 60250
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	
Comparative Tracking Index	225 V	225 V	IEC 60112

Descriptive Properties	Value	Comments
Ball Pressure Test, 125°C +/- 2°C	PASSES	IEC 60695-10-2
UV-light, water exposure/immersion	F1	UL 746C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China