

SABIC Innovative Plastics Lexan® 955A PC (Asia Pacific)

Category : Polymer , Thermoplastic , Polycarbonate (PC)

Material Notes:

Lexan® 955A Polycarbonate (PC) resin is a non-filled, injection moldable grade. This non-chlorinated, non-brominated flame retardant PC has an UL-94 V0 rating. Lexan 955A resin is available in transparent and tinted color options and is a general-purpose resin that is an excellent candidate for a wide variety of applications.

Order this product through the following link:

http://www.lookpolymers.com/polymer_SABIC-Innovative-Plastics-Lexan-955A-PC-Asia-Pacific.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0060 - 0.0080 cm/cm @Thickness 3.20 mm	0.0060 - 0.0080 in/in @Thickness 0.126 in	SABIC Method
Melt Flow	7.0 g/10 min @Load 1.20 kg, Temperature 300 °C	7.0 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	67.0 MPa	9720 psi	Type I, 50 mm/min; ASTM D638
Tensile Strength, Yield	62.0 MPa	8990 psi	Type I, 50 mm/min; ASTM D638
Elongation at Break	125 %	125 %	Type I, 50 mm/min; ASTM D638
Elongation at Yield	6.0 %	6.0 %	Type I, 50 mm/min; ASTM D638
Tensile Modulus	2.27 GPa	329 ksi	50 mm/min; ASTM D638
Flexural Yield Strength	101 MPa	14600 psi	1.3 mm/min, 50 mm span; ASTM D790
Flexural Modulus	2.37 GPa	344 ksi	1.3 mm/min, 50 mm span; ASTM D790
Izod Impact, Notched	8.01 J/cm	15.0 ft-lb/in	ASTM D256
Dart Drop, Total Energy	79.0 J @Temperature 23.0 °C	58.3 ft-lb @Temperature 73.4 °F	ASTM D3763

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	68.4 µm/m-°C @Temperature -40.0 - 40.0 °C	38.0 µin/in-°F @Temperature -40.0 - 104 °F	ASTM E 831

Thermal Properties	Metric	English	Comments
CTE, linear, Transverse to Flow	77.2 mm/m-°C @Temperature -40.0 - 40.0 °C	27.7 in/in-°F @Temperature -40.0 - 104 °F	ASTM E 831
Deflection Temperature at 0.46 MPa (66 psi)	137 °C @Thickness 3.20 mm	279 °F @Thickness 0.126 in	unannealed; ASTM D648
Deflection Temperature at 1.8 MPa (264 psi)	126 °C @Thickness 3.20 mm	259 °F @Thickness 0.126 in	unannealed; ASTM D648
Vicat Softening Point	143 °C	289 °F	Rate B/50; ASTM D1525
UL RTI, Electrical	130 °C	266 °F	UL 746B
UL RTI, Mechanical with Impact	120 °C	248 °F	UL 746B
UL RTI, Mechanical without Impact	130 °C	266 °F	UL 746B
Flammability, UL94	V-2 @Thickness 1.52 mm	V-2 @Thickness 0.0598 in	UL 94
	V-0 @Thickness 3.04 mm	V-0 @Thickness 0.120 in	UL 94
Glow Wire Test	875 °C	1610 °F	IEC 60695-2-13
	960 °C @Thickness 1.00 mm	1760 °F @Thickness 0.0394 in	IEC 60695-2-12

Optical Properties	Metric	English	Comments
Haze	1.0 % @Thickness 2.54 mm	1.0 % @Thickness 0.100 in	ASTM D1003
Transmission, Visible	>= 85 %	>= 85 %	2.54 mm; ASTM D1003

Electrical Properties	Metric	English	Comments
Arc Resistance	0.00 - 60 sec	0.00 - 60 sec	Tungsten; ASTM D495
Comparative Tracking Index	250 - 400 V	250 - 400 V	UL 746A
Hot Wire Ignition, HWI	15 - 30 sec	15 - 30 sec	UL 746A
High Amp Arc Ignition, HAI	15 - 30 arcs	15 - 30 arcs	UL 746A
High Voltage Arc-Tracking Rate, HVTR	80.0 - 150 mm/min	3.15 - 5.91 in/min	UL 746A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China